WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Area

[562094 COVANTA] Wachine Id VOLVO L220H 3339



VOLVO AUTOMATIC TRANSMISSION FLUID AT102 (--- GAL)

VOLVO AUTOMATIC TRANSM	IISSION FLUI	DAI	102 ((GAL)			
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP450708		
	Sample Date		Client Info		21 May 2024		
	Machine Age	hrs	Client Info		9447		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>160	54		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>5	<1		
	Nickel	ppm	ASTM D5185m	>5	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>5	0		
	Aluminum	ppm	ASTM D5185m	>50	2		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>225	12		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	6		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m	187	58		
	Barium	ppm	ASTM D5185m	0.0	3		
	Molybdenum	ppm	ASTM D5185m	0.0	<1		
	Manganese	ppm	ASTM D5185m	0.0	3		
	Magnesium	ppm	ASTM D5185m	6.8	<1		
	Calcium	ppm	ASTM D5185m	215	85		
	Phosphorus	ppm	ASTM D5185m	445	214		
	Zinc	ppm	ASTM D5185m		24		
	Sulfur	ppm	ASTM D5185m		1683		
	Visc @ 40°C	cSt	ASTM D445	35.3	27.9		





Certificate L2367

Laboratory Sample No.

Lab Number : 06195825 Unique Number : 11057948

: VCP450708 Test Package : MOB 1 To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 30 May 2024 **Tested** : 31 May 2024

Diagnosed : 31 May 2024 - Wes Davis 5210 REESE ROAD DAVIE, FL US 33314

Contact: N. FACEY nfacey@altaequipfl.com T: (954)581-4744

ALTA EQUIPMENT COMPANY

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (954)583-0318