



WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	NORMAL

Area
[W67085]

Machine Id
JOHN DEERE 331G 1T0331GKJNF421531

Component
Hydraulic System

Fluid
JOHN DEERE HYDRAU (7 GAL)

RECOMMENDATION

The oil change at the time of sampling has been noted. We recommend you service the filters on this component. Resample at the next service interval to monitor. (Customer Sample Comment: W67085)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0215622	---	---
Sample Date		Client Info		28 May 2024	---	---
Machine Age	hrs	Client Info		1114	---	---
Oil Age	hrs	Client Info		1114	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		N/A	---	---
Sample Status				ABNORMAL	---	---

WEAR

All component wear rates are normal.

PQ		ASTM D8184		18	---	---
Iron	ppm	ASTM D5185m	>20	13	---	---
Chromium	ppm	ASTM D5185m	>10	<1	---	---
Nickel	ppm	ASTM D5185m	>10	0	---	---
Titanium	ppm	ASTM D5185m		0	---	---
Silver	ppm	ASTM D5185m		<1	---	---
Aluminum	ppm	ASTM D5185m	>10	2	---	---
Lead	ppm	ASTM D5185m	>10	<1	---	---
Copper	ppm	ASTM D5185m	>75	6	---	---
Tin	ppm	ASTM D5185m	>10	0	---	---
Vanadium	ppm	ASTM D5185m		<1	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION











There is a high amount of particulates present in the oil.

Silicon	ppm	ASTM D5185m	>20	4	---	---
Potassium	ppm	ASTM D5185m	>20	1	---	---
Water		WC Method	>0.1	NEG	---	---
Particles >4µm		ASTM D7647	>5000	▲ 9992	---	---
Particles >6µm		ASTM D7647	>1300	▲ 4678	---	---
Particles >14µm		ASTM D7647	>160	▲ 910	---	---
Particles >21µm		ASTM D7647	>40	▲ 290	---	---
Particles >38µm		ASTM D7647	>10	5	---	---
Particles >71µm		ASTM D7647	>3	1	---	---
Oil Cleanliness		ISO 4406 (c)	>19/17/14	▲ 20/19/17	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.1	NEG	---	---

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		1	---	---
Boron	ppm	ASTM D5185m		<1	---	---
Barium	ppm	ASTM D5185m		1	---	---
Molybdenum	ppm	ASTM D5185m		<1	---	---
Manganese	ppm	ASTM D5185m		<1	---	---
Magnesium	ppm	ASTM D5185m		6	---	---
Calcium	ppm	ASTM D5185m	87	884	---	---
Phosphorus	ppm	ASTM D5185m	727	795	---	---
Zinc	ppm	ASTM D5185m	900	1013	---	---
Sulfur	ppm	ASTM D5185m	1500	2780	---	---
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.78	---	---
Visc @ 40°C	cSt	ASTM D445	65	48.8	---	---



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0215622 **Received** : 30 May 2024
Lab Number : 06195863 **Tested** : 02 Jun 2024
Unique Number : 11057986 **Diagnosed** : 02 Jun 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

CARLTON'S BACKHOE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: LEO

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (704)547-0211

F: