WEAR CONTAMINATION **FLUID CONDITION** **NORMAL NORMAL NORMAL**

Machine Id


HAMM H5I H222-2170

Component

Hydraulic System

Fluid

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		JR0210203		
Resample at the next service interval to monitor.	Sample Date		Client Info		24 May 2024		
	Machine Age	hrs	Client Info		183		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
VEAR	PQ		ASTM D8184		16		
VEAN	Iron	nnm	ASTM D5185m	>20	2		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5165III	>10	0		
	Silver	ppm			-		
		ppm	ASTM D5185m	× 10	0		
	Aluminum Lead	ppm	ASTM D5185m ASTM D5185m		0 1		
		ppm					
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NONE	<1 NONE		
	White Metal Yellow Metal	scalar scalar	*Visual	NONE	NONE NONE		
<u> </u>							
CONTAMINATION	Silicon	ppm	ASTM D5185m		2		
The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Water		WC Method		NEG		
	Particles >4µm		ASTM D7647		808		
	Particles >6µm		ASTM D7647		208		
	Particles >14μm		ASTM D7647		21		
	Particles >21μm		ASTM D7647		7		
	Particles >38μm		ASTM D7647		0		
	Particles >71μm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		17/15/12		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
	Boron	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		31		
	Phosphorus	ppm	ASTM D5185m		272		
	Zinc	ppm	ASTM D5185m		348		
	Sulfur	ppm	ASTM D5185m		1053		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.27		
	Visc @ 40°C	cSt	ASTM D445		45.2		





Certificate L2367

Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0210203 : 06195866

Received **Tested** Unique Number: 11057989 Diagnosed

: 02 Jun 2024 : 02 Jun 2024 - Don Baldridge Test Package : CONST (Additional Tests: PQ)

: 30 May 2024

JRE - STEPHENSON 245 YARDMASTER COURT STEPHENSON, VA US 22656-1761 Contact: PHIL DAUGHERTY

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. pdaugherty@jamesriverequipment.com T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (540)869-0549