



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 350P 1FF350PATPF000479
 Component
Right Final Drive
 Fluid
JOHN DEERE GL-5 80W90 (9 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0214110	JR0202528	JR0183294
Sample Date		Client Info		29 May 2024	27 Feb 2024	03 Jan 2024
Machine Age	hrs	Client Info		1549	1028	1027
Oil Age	hrs	Client Info		1549	1028	1027
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	233	224	232
Iron	ppm	ASTM D5185m	>750	17	292	301
Chromium	ppm	ASTM D5185m	>9	<1	4	3
Nickel	ppm	ASTM D5185m	>10	2	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>40	2	1	<1
Lead	ppm	ASTM D5185m	>15	0	0	0
Copper	ppm	ASTM D5185m	>40	1	0	0
Tin	ppm	ASTM D5185m	>10	<1	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	<1	17	20
Potassium	ppm	ASTM D5185m	>20	<1	<1	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	MODER	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	5	0	<1
Boron	ppm	ASTM D5185m		26	75	73
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		<1	0	5
Manganese	ppm	ASTM D5185m		<1	6	5
Magnesium	ppm	ASTM D5185m		4	0	<1
Calcium	ppm	ASTM D5185m		17	8	194
Phosphorus	ppm	ASTM D5185m		545	535	555
Zinc	ppm	ASTM D5185m		29	<1	67
Sulfur	ppm	ASTM D5185m		13547	15559	15238
Visc @ 40°C	cSt	ASTM D445		184	187	185



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0214110 **Received** : 30 May 2024
Lab Number : 06196041 **Tested** : 31 May 2024
Unique Number : 11058164 **Diagnosed** : 02 Jun 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

JRE - NEW BERN
 3816 MARTIN LUTHER KING BLVD
 NEW BERN, NC
 US 28562
 Contact: NEW BERN SHOP

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

nick.etherdridge@jamesriverequipment.com; canastasio@wearcheckusa.com

T:
F: