



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
HAMM H2840111
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0217614	JR0182040	JR0137125
Sample Date		Client Info		31 May 2024	01 Aug 2023	20 Jul 2022
Machine Age	hrs	Client Info		2073	436	436
Oil Age	hrs	Client Info		0	436	0
Filter Age	hrs	Client Info		0	436	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	64	24	21
Chromium	ppm	ASTM D5185m	>20	1	1	1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	8	3	3
Lead	ppm	ASTM D5185m	>40	15	1	3
Copper	ppm	ASTM D5185m	>330	6	5	11
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	23	16	24
Potassium	ppm	ASTM D5185m	>20	<1	1	<1
Fuel		WC Method	>5	<1.0	<1.0	0.2
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.7	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	10.8	9.5	10.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	27.4	23.3	20.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	2	3
Boron	ppm	ASTM D5185m		63	145	47
Barium	ppm	ASTM D5185m		<1	<1	<1
Molybdenum	ppm	ASTM D5185m		239	220	78
Manganese	ppm	ASTM D5185m		2	<1	2
Magnesium	ppm	ASTM D5185m		793	740	122
Calcium	ppm	ASTM D5185m		1638	1571	2101
Phosphorus	ppm	ASTM D5185m		1032	861	938
Zinc	ppm	ASTM D5185m		1248	1096	1206
Sulfur	ppm	ASTM D5185m		3552	3614	4811
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.2	17.9	15.7
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	7.3	7.7	7.2
Visc @ 100°C	cSt	ASTM D445	15.4	12.8	12.9	12.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0217614 **Received** : 31 May 2024
Lab Number : 06196382 **Tested** : 03 Jun 2024
Unique Number : 11058505 **Diagnosed** : 03 Jun 2024 - Don Baldrige
Test Package : CONST (Additional Tests: TBN)

B & S SITE DEVELOPMENT
 7800 PINEY BRANCH LANE
 BRISTOW, VA
 US 20136
 Contact: DANNY HUFF
 dhuff@bandssite.com
 T: (540)270-3203
 F: (703)753-0605

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)