



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
Store 9 - Marietta
Machine Id
JOHN DEERE 210G 1FF210GXTNF530413
Component
Diesel Engine
Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (6 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0048966	LEC0043828	LEC0038932
Sample Date		Client Info		21 May 2024	15 Aug 2023	17 Mar 2023
Machine Age	hrs	Client Info		1964	1184	523
Oil Age	hrs	Client Info		500	661	523
Filter Age	hrs	Client Info		500	661	523
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	39	51	46
Chromium	ppm	ASTM D5185m	>11	<1	2	1
Nickel	ppm	ASTM D5185m	>5	6	▲ 9	5
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	3	<1	4
Lead	ppm	ASTM D5185m	>26	0	2	<1
Copper	ppm	ASTM D5185m	>26	13	▲ 62	▲ 348
Tin	ppm	ASTM D5185m	>4	1	1	2
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>120	6	11	11
Potassium	ppm	ASTM D5185m	>20	0	1	2
Fuel		WC Method	>2.1	<1.0	<1.0	0.7
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.7	0.9	0.4
Nitration	Abs/cm	*ASTM D7624	>20	9.5	11.7	10.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.3	27.1	24.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	4	6	6
Boron	ppm	ASTM D5185m		99	69	190
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		97	270	228
Manganese	ppm	ASTM D5185m		1	2	4
Magnesium	ppm	ASTM D5185m		774	884	823
Calcium	ppm	ASTM D5185m		1362	1750	1496
Phosphorus	ppm	ASTM D5185m		1002	926	810
Zinc	ppm	ASTM D5185m		1228	1170	1003
Sulfur	ppm	ASTM D5185m		3071	3517	3037
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.1	23.0	20.3
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	7.0	8.1	8.0
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	13.75	● 10.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0048966 **Received** : 31 May 2024
Lab Number : 06196417 **Tested** : 02 Jun 2024
Unique Number : 11058540 **Diagnosed** : 02 Jun 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LANE PIPELINE
 2946 E MAIN ST
 BRIDGEPORT, WV
 US 26330

Contact: JESSE WILBURN
 jessewilburn@gmail.com

T: (740)440-0927

F: