

## Machine Id **25407** Component **Diesel Engine** Fluid **DIESEL ENGINE OIL SAE 15W40 (--- QTS)**

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0925981		
	Sample Date		Client Info		24 May 2024		
	Machine Age	mls	Client Info		21189		
	Oil Age	mls	Client Info		0		
	Filter Age	mls	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
				100			
WEAR Metal levels are typical for a new component breaking in.	Iron Chromium	ppm	ASTM D5185m ASTM D5185m		17 <1		
		ppm			< 1 0		
	Nickel	ppm	ASTM D5185m ASTM D5185m	>4			
	Titanium	ppm		0	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	> 25	6		
CONTAMINATION	Potassium	ppm	ASTM D5185m		7		
There is no indication of any contamination in the oil.	Fuel	ppm					
			WC Method	>5	<1.0 NEG		
	Water		WC Method WC Method	>0.2			
	Glycol	0/		0	NEG		
	Soot %	%	*ASTM D7844		0.3		
	Nitration	Abs/cm	*ASTM D7624	>20	7.4		
	Sulfation	Abs/.1mm	*ASTM D7415		22.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>158	1		
	Boron	ppm	ASTM D5185m		376		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		81		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	450	454		
	Calcium	ppm	ASTM D5185m	3000	1324		
	Phosphorus	ppm	ASTM D5185m		1067		
	Zinc			1350	1262		
	Sulfur	ppm ppm	ASTM D5185m		3563		
			*ASTM D5185111 *ASTM D7414				
	Oxidation	AUS/.IMM	ASTIVI D/414	>20	16.6		

Base Number (BN) mg KOH/g ASTM D2896 8.5

ASTM D445 14.4

Visc @ 100°C cSt

7.4

13.3



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 SALEM NATIONALEASE CORPORATION Sample No. Received 198 PARK PLAZA DRIVE : WC0925981 : 31 May 2024 Lab Number : 06196516 Tested WINSTON SALEM, NC : 03 Jun 2024 Diagnosed Unique Number : 11058639 : 03 Jun 2024 - Wes Davis US 27105 Test Package : FLEET **Contact: Audrey Hopkins** Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. Audrey.Hopkins@salemcorp.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (336)767-9642 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: x:

Report Id: SALWIN [WUSCAR] 06196516 (Generated: 06/04/2024 07:16:20) Rev: 1

Ġ

Contact/Location: Audrey Hopkins - SALWIN Page 2 of 2