



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH T800 ST40 (S/N 254337)
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL 10W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		HPL0004305	HPL0004136	HPL0002737
Sample Date		Client Info		29 May 2024	28 Jan 2024	09 Oct 2023
Machine Age	hrs	Client Info		4303	3508	2759
Oil Age	hrs	Client Info		0	0	750
Filter Age	hrs	Client Info		0	0	750
Oil Changed		Client Info		N/A	N/A	Changed
Filter Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	26	25	22
Chromium	ppm	ASTM D5185m	>20	2	2	2
Nickel	ppm	ASTM D5185m	>4	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	21	20	37
Lead	ppm	ASTM D5185m	>40	2	1	2
Copper	ppm	ASTM D5185m	>330	3	3	6
Tin	ppm	ASTM D5185m	>15	1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	14	14	13
Potassium	ppm	ASTM D5185m	>20	38	45	93
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	11.4	14.0	14.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	32.2	40.0	41.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	0	1
Boron	ppm	ASTM D5185m	250	0	<1	0
Barium	ppm	ASTM D5185m	10	4	3	12
Molybdenum	ppm	ASTM D5185m	100	626	556	604
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m	450	1017	941	926
Calcium	ppm	ASTM D5185m	3000	2705	2413	2433
Phosphorus	ppm	ASTM D5185m	1150	1183	1003	1038
Zinc	ppm	ASTM D5185m	1350	1331	1194	1263
Sulfur	ppm	ASTM D5185m	4250	8277	8508	9276
Oxidation	Abs/.1mm	*ASTM D7414	>25	31.7	44.7	45.8
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	11.83	12.49	11.73
Visc @ 100°C	cSt	ASTM D445	14.4	13.7	13.5	13.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : HPL0004305
Lab Number : 06196877
Unique Number : 11059000
Test Package : MOB 2

Received : 31 May 2024
Tested : 03 Jun 2024
Diagnosed : 03 Jun 2024 - Sean Felton

STEVENS ON CRANE
 410 STEVENSON DR
 BOLINGBROOK, IL
 US 60440

Contact: DAVE KOEHNE
 davidk@stevensoncrane.com

T: (630)972-9199

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)