

## WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



## Store 3 - Norton JOHN DEERE 135P 1FF135PACPF000448

Swing Drive

JOHN DEERE GL-5 80W90 (3 QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0050116		
nesample at the next service interval to monitor.	Sample Date		Client Info		29 May 2024		
	Machine Age	hrs	Client Info		616		
	Oil Age	hrs	Client Info		616		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		50		
	Iron	ppm	ASTM D0104 ASTM D5185m	<151	71		
All component wear rates are normal.	Chromium		ASTM D5185m		<1		
	Nickel	ppm ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	210	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>21	0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m	-	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		28		
	Potassium	ppm	ASTM D5185m		1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor Emulsified Water	scalar	*Visual	NORML	NORML		
		scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		98		
	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		12		
	Phosphorus	ppm	ASTM D5185m		577		
	Zinc	ppm	ASTM D5185m		6		
	Sulfur	ppm	ASTM D5185m		18151		

Visc @ 40°C


cSt

ASTM D445

Submitted By: STORE 3 - NORTON - BRIAN YOUTZY

186





Submitted By: STORE 3 - NORTON - BRIAN YOUTZY Page 2 of 2