



WEAR CONTAMINATION FLUID CONDITION

SEVERE SEVERE NORMAL



Machine Id JOHN DEERE 210G 1FF210GXVKF527613

Right Propel Gearbox							
GEAR OIL SAE 90 (2 GAL)							
RECOMMENDATION	T		Mathaad	Line it / Alexa		I Batamid	l listam o
We advise that you check all areas where dirt can enter the system. We recommend that you drain the oil from the component if this has not already been done. We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		LEC0049028		LEC0026931
	Sample Date	lawa	Client Info		24 May 2024	23 Jul 2023	30 Dec 2021
	Machine Age	hrs	Client Info		4179	3574	2280
	Oil Age Filter Age	hrs	Client Info		500 0	1294	397 0
	Oil Changed	1115	Client Info		Not Changd	Changed	Changed
	Filter Changed		Client Info		Changed	None	N/A
	Sample Status		Olletti IIIIO		SEVERE	SEVERE	NORMAL
WEAR	PQ		ASTM D8184		2044	683	83
Gear wear is indicated.	Iron	ppm	ASTM D5185m	>1250	▲ 5198	<u>^</u> 2814	100
	Chromium	ppm	ASTM D5185m	>10	▲ 39	<u>^</u> 23	1
	Nickel	ppm	ASTM D5185m	>10	6	3	0
	Titanium	ppm	ASTM D5185m		26	25	<1
	Silver	ppm	ASTM D5185m		0	<1	0
	Aluminum	ppm	ASTM D5185m		<u>231</u>	326	4
	Lead	ppm	ASTM D5185m		0	0	0
	Copper	ppm	ASTM D5185m		11	3	<1
	Tin	ppm	ASTM D5185m		<1	0	<1
	Vanadium	ppm	ASTM D5185m		1	1	<1
	White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m		1411	1 294	16
Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress. The water content is negligible.	Potassium	ppm	ASTM D5185m	>20	61	89	1
	Water	%	ASTM D6304	>0.2	0.153		
	ppm Water	ppm	ASTM D6304	>2000	1530		
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	0.2%	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		10	10	<1
The oil is no longer serviceable due to the presence of contaminants.	Boron	ppm	ASTM D5185m	400	167	12	9
	Barium	ppm	ASTM D5185m	200	1	2	0
	Molybdenum	ppm	ASTM D5185m	12	8	3	3
	Manganese	ppm	ASTM D5185m		38	28	1
	Magnesium	ppm	ASTM D5185m	12	41	115	104
	Calcium	ppm	ASTM D5185m	150	642	3196	3478
	Phosphorus	ppm	ASTM D5185m	1650	1078	926	1016
	Zinc	ppm	ASTM D5185m	125	255	1049	1230

Sulfur

Visc @ 40°C

ASTM D5185m 22500

ASTM D445 183

ppm

cSt


19414

3683

56.0

Submitted By: JEFF SHERRY

3772





Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 06197022

: LEC0049028

Received **Tested** Unique Number: 11059145

Diagnosed Test Package : CONST (Additional Tests: KF, PQ)

: 04 Jun 2024 : 04 Jun 2024 - Sean Felton

: 31 May 2024

BRIDGEPORT, WV US 26330 Contact: JESSE WILBURN

jesseowilburn@gmail.com T: (740)440-0927

LANE PIPELINE

2946 E MAIN ST

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: