



LIEBHERR L566 014293-460

Rear Differential

GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LH0264550	LHMC012365	
Sample Date		Client Info		24 May 2024	23 Mar 2007	
Machine Age	hrs	Client Info		33900	1022	
Oil Age	hrs	Client Info		0	1022	
Filter Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Not Changd	Changed	
Filter Changed		Client Info		Not Changd	N/A	
Sample Status				NORMAL	NORMAL	
Iron	ppm	ASTM D5185m	>800	260	123	
Chromium	ppm	ASTM D5185m	>10	1	2	
Nickel	ppm	ASTM D5185m	>4	0	<1	
Titanium	ppm	ASTM D5185m	>8	0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>20	0	<1	
Lead	ppm	ASTM D5185m	>10	0	0	
Copper	ppm	ASTM D5185m	>100	1	5	
Tin	ppm	ASTM D5185m	>5	0	0	
Vanadium	ppm	ASTM D5185m		0	0	
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Silicon	ppm	ASTM D5185m	>75	4	9	
Potassium	ppm	ASTM D5185m	>20	<1	0	
Water		WC Method	>.2	NEG	NEG	
Silt	scalar	*Visual	NONE	NONE	LIGHT	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	
Sodium		ASTM D5185m	>170	1	3	
Boron	ppm ppm	ASTM D5185m	400	43	5	
Barium	ppm	ASTM D5185m	200	0	3	
Molybdenum	ppm	ASTM D5185m	12	9	18	
Manganese	ppm	ASTM D5185m	12	2	4	
Manganese	ppm	ASTM D5185m	12	6	0	
Calcium	ppm	ASTM D5185m	150	33	5	
Phosphorus	ppm	ASTM D5185m	1650	2159	1959	
Zinc	ppm	ASTM D5185m	125	11	4	
Sulfur	ppm	ASTM D5185m	22500	29652	28700	
Visc @ 40°C	cSt	ASTM D3183m ASTM D445	143	177	187.9	
130 @ 40 0	601	A0 I WI D440	140		107.5	

Contact/Location: MARK SNYDER - DOMWAU





DOMTAR PULP AND PAPER Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received : 31 May 2024 301 POINT BASSE AVE : LH0264550 Lab Number : 06197085 Tested : 03 Jun 2024 NEKOOSA, WI Unique Number : 11059208 Diagnosed : 03 Jun 2024 - Wes Davis US 54457 Test Package : CONST Contact: MARK SNYDER Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. mark.snyder@domtar.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (715)675-6900 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (715)675-9748

Contact/Location: MARK SNYDER - DOMWAU Page 2 of 2