



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
FREIGHTLINER 1233
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0917203	WC0906147	WC0906088
Sample Date		Client Info		01 May 2024	07 Apr 2024	14 Mar 2024
Machine Age	mls	Client Info		136602	131904	100866
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	0	10	13
Chromium	ppm	ASTM D5185m	>5	<1	2	1
Nickel	ppm	ASTM D5185m	>2	0	1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>30	2	5	4
Lead	ppm	ASTM D5185m	>30	0	1	0
Copper	ppm	ASTM D5185m	>150	1	4	1
Tin	ppm	ASTM D5185m	>5	0	1	0
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	0	4	4
Potassium	ppm	ASTM D5185m	>20	2	11	6
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.5	0.5
Nitration	Abs/cm	*ASTM D7624	>20	5.9	7.5	8.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.1	19.0	19.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	1	<1	<1
Boron	ppm	ASTM D5185m	250	0	1	0
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	57	56	64
Manganese	ppm	ASTM D5185m		0	1	<1
Magnesium	ppm	ASTM D5185m	450	931	888	1091
Calcium	ppm	ASTM D5185m	3000	1143	1056	1224
Phosphorus	ppm	ASTM D5185m	1150	1027	958	1143
Zinc	ppm	ASTM D5185m	1350	1233	1194	1369
Sulfur	ppm	ASTM D5185m	4250	3553	3232	3678
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.6	14.6	15.5
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.0	8.2	8.5
Visc @ 100°C	cSt	ASTM D445	14.4	14.2	14.1	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0917203 **Received** : 03 Jun 2024
Lab Number : 06197260 **Tested** : 03 Jun 2024
Unique Number : 11059383 **Diagnosed** : 03 Jun 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

CONCRETE SERVICE CO - FAY BLOCK
 161 BUILDERS BLVD
 FAYETTEVILLE, NC
 US 28301
 Contact: BRYAN VANNIMAN
 bryanvanniman@fayblock.com
 T: (800)326-9198
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)