WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area


[SPM716708 WASTE MGMT]

VOLVO L150H 633423

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		VCP439873		
Resample at the next service interval to monitor.	Sample Date		Client Info		21 May 2024		
	Machine Age	hrs	Client Info		1956		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	nnm	ASTM D5185m	× 100	11		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m	>10	<1		
	Silver		ASTM D5185m	~2	<1		
	Aluminum	ppm	ASTM D5185m		5		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		1		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	4		
There is no indication of any contamination in the oil	Potassium	ppm	ASTM D5185m	>20	1		
There is no indication of any contamination in the oil.	Fuel		WC Method	>6.0	<1.0		
	Water		WC Method	>0.1	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	6.3		
	Sulfation	Abs/.1mm	*ASTM D7415		18.4		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>158	3		
	Boron	ppm	ASTM D5185m		0		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		61		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m	450	1049		
	Calcium	ppm		3000	1054		
	Phosphorus	ppm	ASTM D5185m	1150	1094		
	Zinc	ppm	ASTM D5185m	1350	1327		
	Sulfur	ppm	ASTM D5185m	4250	3567		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3		
	Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.6		
	Visc @ 100°C	cSt	ASTM D445	14.4	13.5		





Laboratory Sample No.

Lab Number : 06197397 Unique Number : 11059520

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : VCP439873

Received **Tested** Diagnosed

: 03 Jun 2024 : 04 Jun 2024

: 04 Jun 2024 - Wes Davis

ALTA EQUIPMENT CO - ORLAND PARK 5000 INDUSTRIAL HWY GARY, IN

US 46406 Contact: MARK DEROSA mark.derosa@altg.com T: (248)356-5200

Test Package : MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)