



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 1T0410LXLKF350371
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (14 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0217879	JR0169107	JR0140109
Sample Date		Client Info		30 May 2024	21 Apr 2023	17 Aug 2022
Machine Age	hrs	Client Info		1614	1404	1115
Oil Age	hrs	Client Info		210	1404	216
Filter Age	hrs	Client Info		210	1404	216
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	15	12	8
Chromium	ppm	ASTM D5185m	>11	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	7	3	3
Lead	ppm	ASTM D5185m	>26	2	0	1
Copper	ppm	ASTM D5185m	>26	2	1	2
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	9	8	6
Potassium	ppm	ASTM D5185m	>20	3	0	2
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.5	9.1	9.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.0	20.4	22.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	1	2	<1
Boron	ppm	ASTM D5185m		401	254	258
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		362	263	261
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		1144	840	775
Calcium	ppm	ASTM D5185m		1932	1424	1441
Phosphorus	ppm	ASTM D5185m		1329	901	922
Zinc	ppm	ASTM D5185m		1549	1142	1102
Sulfur	ppm	ASTM D5185m		4825	3327	3208
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.8	16.5	17.3
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.7	7.6	10.0
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	13.1	13.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0217879
Lab Number : 06197447
Unique Number : 11059570
Test Package : CONST (Additional Tests: TBN)

Received : 03 Jun 2024
Tested : 04 Jun 2024
Diagnosed : 04 Jun 2024 - Don Baldrige

NPL CONSTRUCTION
 7611 COPPERMINE DR
 MANASSAS, VA
 US 20109-2668
 Contact: BRANDON

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: