WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

## NO INFO ON SIF/BOTTLE

Diesel Engine

{not provided} (--- GAL)

{iiot provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0212654		
	Sample Date		Client Info		02 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	nnm	ACTM DE10Em	. 100	45		
	Chromium	ppm	ASTM D5185m		15 .•		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1		
		ppm	ASTM D5185m	>4	2		
	Titanium	ppm	ASTM D5185m	0	<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	7		
	Potassium	ppm	ASTM D5185m	>20	2		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.3		
	Nitration	Abs/cm	*ASTM D7624	>20	9.2		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	22.2		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		250		
	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		268		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		834		
	Calcium	ppm	ASTM D5185m		1449		
	Phosphorus	ppm	ASTM D5185m		984		
	Zinc	ppm	ASTM D5185m		1145		
	Sulfur	ppm	ASTM D5185m		3336		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	17.1		
	Oxidation						
	Base Number (BN)		ASTM D2896		8.6		





Report Id: RWMGAR [WUSCAR] 06197457 (Generated: 06/04/2024 13:48:41) Rev: 1

Laboratory Sample No.

Lab Number : 06197457 Unique Number : 11059580 Test Package : CONST (Additional Tests: TBN)

: JR0212654

Received **Tested** Diagnosed

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 03 Jun 2024 : 04 Jun 2024

: 04 Jun 2024 - Don Baldridge

JRE - GARNER 4161 AUBURN CHURCH RD GARNER, NC

US 27529 Contact: RALEIGH SHOP

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. sean.betts@jamesriverequipment.com;catherine.anastasio@wearcheck.com T: (919)614-2260 F: (919)779-5432