



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 1T0310SLCMF397280
 Component
Hydraulic System
 Fluid
JOHN DEERE HYDRAU (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0218018	JR0170016	JR0174678
Sample Date		Client Info		30 May 2024	01 Aug 2023	25 May 2023
Machine Age	hrs	Client Info		1248	1069	972
Oil Age	hrs	Client Info		1248	2	972
Filter Age	hrs	Client Info		1248	2	972
Oil Changed		Client Info		Not Changed	N/A	Not Changed
Filter Changed		Client Info		Not Changed	N/A	Not Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

PQ	UOM	Method	Limit/Abn	Current	History1	History2
Iron	ppm	ASTM D5185m	>20	0	2	6
Chromium	ppm	ASTM D5185m	>10	2	2	5
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m		0	<1	0
Aluminum	ppm	ASTM D5185m	>10	<1	<1	0
Lead	ppm	ASTM D5185m	>10	0	1	0
Copper	ppm	ASTM D5185m	>75	<1	<1	2
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	0	2	4
Potassium	ppm	ASTM D5185m	>20	4	6	12
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>5000	3840	1610	7202
Particles >6µm		ASTM D7647	>1300	957	421	350
Particles >14µm		ASTM D7647	>160	87	26	23
Particles >21µm		ASTM D7647	>40	20	7	5
Particles >38µm		ASTM D7647	>10	1	1	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/17/14	18/16/12	20/16/12
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	1	3
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	1	0
Molybdenum	ppm	ASTM D5185m		0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		13	6	14
Calcium	ppm	ASTM D5185m	87	587	185	295
Phosphorus	ppm	ASTM D5185m	727	728	655	665
Zinc	ppm	ASTM D5185m	900	902	893	892
Sulfur	ppm	ASTM D5185m	1500	2166	2006	1827
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.75	0.93	0.71
Visc @ 40°C	cSt	ASTM D445	65	58.2	59.88	57.9



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0218018 **Received** : 03 Jun 2024
Lab Number : 06197537 **Tested** : 04 Jun 2024
Unique Number : 11059660 **Diagnosed** : 04 Jun 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

NPL CONSTRUCTION
 7611 COPPERMINE DR
 MANASSAS, VA
 US 20109-2668
 Contact: BRANDON

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)