



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
(YA150011)
Machine Id
10887C
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (8 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0123505	GFL0109509	GFL0058813
Sample Date		Client Info		13 Jun 2024	15 Feb 2024	05 May 2023
Machine Age	hrs	Client Info		32695	20300	0
Oil Age	hrs	Client Info		1200	1200	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	7	25	10
Chromium	ppm	ASTM D5185m	>20	<1	3	1
Nickel	ppm	ASTM D5185m	>2	0	<1	1
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	4	0
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	1	1	0
Tin	ppm	ASTM D5185m	>15	<1	<1	1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	10	12
Potassium	ppm	ASTM D5185m	>20	1	3	2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	5.5	11.2	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6	21.4	18.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	6	3
Boron	ppm	ASTM D5185m	0	58	12	25
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	42	55	52
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	483	599	635
Calcium	ppm	ASTM D5185m	1070	1247	1568	1439
Phosphorus	ppm	ASTM D5185m	1150	597	748	807
Zinc	ppm	ASTM D5185m	1270	764	1025	987
Sulfur	ppm	ASTM D5185m	2060	2349	2530	3095
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.1	17.1	15.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.0	4.7	7.9
Visc @ 100°C	cSt	ASTM D445	15.4	13.2	14.6	14.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0123505
Lab Number : 06209843
Unique Number : 11082707
Test Package : FLEET

Received : 14 Jun 2024
Tested : 15 Jun 2024
Diagnosed : 17 Jun 2024 - Angela Borella

GFL Environmental - 019 - Greenville/TriEast
 415 Staton Road
 Greenville, NC
 US 27834

Contact: Spencer Ligon
 spencer.ligon@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (800)207-6618

F: