WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


[WNC HARDSCAPE]

## **JOHN DEERE 35P 1FF035PAVPK000891**

Diesel Engine

{not provided} (--- GAL)

	Task	11084	Mada	Linete/All.	<b>O</b>	111:44:00:04	I Bakam O
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0207995		
	Sample Date		Client Info		07 Jun 2024		
	Machine Age	hrs	Client Info		403		
	Oil Age	hrs	Client Info		403		
	Filter Age	hrs	Client Info		403		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	la a a		AOTM DE40E		4-		
WEAR	Iron	ppm	ASTM D5185m		47		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>5	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		5		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		13		
	Tin	ppm	ASTM D5185m	>4	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTABBINATION	0:1:		AOTM DE40E	00	0.4		
CONTAMINATION	Silicon	ppm	ASTM D5185m		64		
Fuel content negligible. There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		4		
	Fuel	%	ASTM D3524		1.5		
	Water		WC Method	>0.21	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844		0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	7.7		
	Sulfation	Abs/.1mm	*ASTM D7415		15.9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual	>0.21	NEG		
LUID CONDITION	C = =!:=		ACTM DE10E	04	00		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>J I	23		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		49		
	Barium	ppm	ASTM D5185m		11		
	Molybdenum	ppm	ASTM D5185m		119		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		28		
	Calcium	ppm	ASTM D5185m		4005		
	Phosphorus	ppm	ASTM D5185m		1006		
	Zinc	ppm	ASTM D5185m		1322		
	Sulfur	ppm	ASTM D5185m		6944		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	9.5		
	Base Number (BN)	mg KOH/g	ASTM D2896		12.1		
	Visc @ 100°C	cSt	ASTM D445		9.5		







Laboratory Sample No.

Lab Number : 06209919

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0207995

Unique Number : 11082783

Received **Tested** Diagnosed

: 14 Jun 2024 : 19 Jun 2024

: 19 Jun 2024 - Jonathan Hester

JRE - ASHEVILLE 101 BRUCE DRIVE ASHEVILLE, NC US 28806

Test Package: CONST (Additional Tests: FuelDilution, PercentFuel, TBN) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Contact: Randy Warren randy.warren@jamesriverequipment.com T: (528)667-0176

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (828)667-4865