WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

Machine Id

JOHN DEERE 624 P 1DW624PACRLX21662

Rear Axle

TDH FLUID SAE 75W80 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0213298		
	Sample Date		Client Info		13 Jun 2024		
	Machine Age	hrs	Client Info		520		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		39		
Metal levels are typical for a new component breaking in.	Iron	ppm	ASTM D5185m	>750	158		
	Chromium	ppm	ASTM D5185m	>11	1		
	Nickel	ppm	ASTM D5185m	>10	1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>21	1		
	Lead	ppm	ASTM D5185m		111		
	Copper	ppm	ASTM D5185m		63		
	Tin	ppm	ASTM D5185m	>10	1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>31	10		
	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	5		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	10	4		
	Barium	ppm	ASTM D5185m	10	7		
	Molybdenum	ppm	ASTM D5185m	10	<1		
	Manganese	ppm	ASTM D5185m		7		
	Magnesium	ppm	ASTM D5185m		99		
	Calcium	ppm	ASTM D5185m	3500	3440		
	Phosphorus	ppm	ASTM D5185m	1150	1105		
	Zinc	ppm	ASTM D5185m		1257		
	Sulfur	ppm	ASTM D5185m		4404		
Papart Id. IAMCDE IMI ISCADI 06910412 (Caparated: 06/99/9094 10:40:45) Pays 1	Visc @ 40°C	cSt	ASTM D445	48	54.7	 CALLAUED	 IAMODE





Certificate L2367

Report Id: JAMGRE [WUSCAR] 06210413 (Generated: 06/22/2024 19:40:47) Rev: 1

Laboratory Sample No.

: JR0213298 Lab Number : 06210413

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Unique Number : 11083277 Diagnosed Test Package : CONST (Additional Tests: PQ)

: 17 Jun 2024 : 18 Jun 2024 - Don Baldridge

: 14 Jun 2024

US 27409 Contact: NICK GALLAHER NGALLAHER@JRENET.COM

T: (336)668-2762 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (336)665-9556

JRE - GREENSBORO

GREENSBORO, NC

411 SOUTH REGIONAL ROAD