



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
STEPHEN P VENABLE
Machine Id
[STEPHEN P VENABLE] 008 590046-8
Component
Starboard Genset
Fluid
CHEVRON DELO 400 LE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0063009	MW0067988	MW0067969
Sample Date		Client Info		01 Jun 2024	22 May 2024	03 Apr 2024
Machine Age	hrs	Client Info		8184	293	7699
Oil Age	hrs	Client Info		437	293	7699
Filter Age	hrs	Client Info		437	293	7699
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	6	6	7
Chromium	ppm	ASTM D5185m	>4	0	0	0
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>5	0	<1	0
Aluminum	ppm	ASTM D5185m	>12	1	2	3
Lead	ppm	ASTM D5185m	>17	0	<1	0
Copper	ppm	ASTM D5185m	>70	<1	0	<1
Tin	ppm	ASTM D5185m	>15	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	5	6
Potassium	ppm	ASTM D5185m	>20	<1	<1	1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.7	6.4	7.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5	19.5	23.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	0	1
Boron	ppm	ASTM D5185m		285	319	316
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		82	92	134
Manganese	ppm	ASTM D5185m		2	2	2
Magnesium	ppm	ASTM D5185m		359	420	724
Calcium	ppm	ASTM D5185m		2157	2282	1773
Phosphorus	ppm	ASTM D5185m	1200	727	806	755
Zinc	ppm	ASTM D5185m	1300	876	977	917
Sulfur	ppm	ASTM D5185m	3200	3072	3463	3251
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.4	13.2	18.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	7.4	7.5	9.3
Visc @ 100°C	cSt	ASTM D445	15.7	13.7	13.5	13.3



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0063009 **Received** : 14 Jun 2024
Lab Number : 06211057 **Tested** : 19 Jun 2024
Unique Number : 11083921 **Diagnosed** : 19 Jun 2024 - Sean Felton
Test Package : MAR 2 (Additional Tests: TAN Man)

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003
 Contact: JOHNNY HINES
 johnny.hines@ingrambarge.com
 T: (270)415-4467
 F: (615)695-3697

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)