



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
MISS SHEILA
Component
Port Genset
Fluid
DIESEL ENGINE OIL SAE 15W40 (4 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0071261	MW0048204	MW0048154
Sample Date		Client Info		07 Jun 2024	11 Apr 2024	13 Dec 2023
Machine Age	hrs	Client Info		18972	18303	16987
Oil Age	hrs	Client Info		669	958	722
Filter Age	hrs	Client Info		669	958	722
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	8	12	15
Chromium	ppm	ASTM D5185m	>4	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>12	2	4	5
Lead	ppm	ASTM D5185m	>17	0	2	4
Copper	ppm	ASTM D5185m	>70	0	1	0
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	6	5
Potassium	ppm	ASTM D5185m	>20	0	2	1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.2	0.6	0.3
Nitration	Abs/cm	*ASTM D7624	>20	6.9	7.4	7.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.3	22.9	23.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	<1	<1	0
Boron	ppm	ASTM D5185m	250	355	429	305
Barium	ppm	ASTM D5185m	10	0	<1	0
Molybdenum	ppm	ASTM D5185m	100	95	137	132
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	450	508	670	706
Calcium	ppm	ASTM D5185m	3000	1730	1641	1563
Phosphorus	ppm	ASTM D5185m	1150	1068	891	765
Zinc	ppm	ASTM D5185m	1350	1320	947	873
Sulfur	ppm	ASTM D5185m	4250	3959	3129	2481
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.2	15.5	17.2
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	6.8	8.2	7.9
Visc @ 100°C	cSt	ASTM D445	14.4	13.6	13.5	13.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0071261
Lab Number : 06211311
Unique Number : 11084175
Test Package : MAR 2

Received : 17 Jun 2024
Tested : 19 Jun 2024
Diagnosed : 19 Jun 2024 - Wes Davis

ARTCO - ADM AG SERVICES & OIL SEEDS
 2505 BLUFF ROAD
 MT VERNON, IN
 US 47620
 Contact: JOE FLOYD
 joseph.floyd@adm.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: