



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[W11693]

Machine Id

JOHN DEERE 35D 1FF035DXECG268707

Component

Diesel Engine

Fluid

DIESEL ENGINE OIL SAE 40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0207333	JR0170404	JR0126169
Sample Date		Client Info		11 Jun 2024	19 Dec 2023	14 Jan 2023
Machine Age	hrs	Client Info		1293	1063	1063
Oil Age	hrs	Client Info		1063	250	0
Filter Age	hrs	Client Info		1063	250	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	10	3	8
Chromium	ppm	ASTM D5185m	>11	0	0	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	5	2	2
Lead	ppm	ASTM D5185m	>26	0	0	<1
Copper	ppm	ASTM D5185m	>26	<1	<1	<1
Tin	ppm	ASTM D5185m	>4	0	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	11	9	7
Potassium	ppm	ASTM D5185m	>20	3	0	0
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.5	7.9	5.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1	20.8	17.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	3	3	1
Boron	ppm	ASTM D5185m	250	229	36	30
Barium	ppm	ASTM D5185m	10	0	<1	0
Molybdenum	ppm	ASTM D5185m	100	220	81	80
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	450	784	473	441
Calcium	ppm	ASTM D5185m	3000	1388	1678	1746
Phosphorus	ppm	ASTM D5185m	1150	918	1076	1019
Zinc	ppm	ASTM D5185m	1350	1063	1237	1181
Sulfur	ppm	ASTM D5185m	4250	3579	3249	3956
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.2	17.2	13.6
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.1	7.6	8.9
Visc @ 100°C	cSt	ASTM D445	14.4	13.3	13.4	13.2



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0207333 **Received** : 17 Jun 2024
Lab Number : 06211425 **Tested** : 18 Jun 2024
Unique Number : 11084289 **Diagnosed** : 18 Jun 2024 - Wes Davis
Test Package : MOBCE (Additional Tests: TBN)

JRE - SALEM
 3902 W. MAIN STREET
 SALEM, VA
 US 24153
 Contact: ROBERT SMITH
 ROBERT.SMITH@JAMESRIVEREQUIPMENT.COM
 T:
 F: (540)380-5547

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)