WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

56076

Hydraulic System

AW HYDRAULIC OIL ISO 32 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TESSIMIERS/CITOR	Sample Number		Client Info		WC0833583	WC0480854	
Resample at the next service interval to monitor.	Sample Date		Client Info		02 Aug 2023	16 Aug 2022	
	Machine Age	hrs	Client Info		2000	2000	
	Oil Age	hrs	Client Info		2000	2000	
	Filter Age	hrs	Client Info		2000	2000	
	Oil Changed		Client Info		N/A	N/A	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>20	9	7	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1	0	
	Nickel	ppm	ASTM D5185m	>10	<1	0	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>10	2	0	
	Lead	ppm	ASTM D5185m		<1	0	
	Copper	ppm	ASTM D5185m		1	<1	
	Tin	ppm	ASTM D5185m	>10	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTABUNATION	0.11.						
CONTAMINATION	Silicon	ppm	ASTM D5185m		2	<1	
There is no indication of any contamination in the oil. The amount and	Potassium	ppm	ASTM D5185m		<1	0	
size of particulates present in the system are acceptable.	Water		WC Method		NEG	NEG	
	Particles >4µm		ASTM D7647		1233	2855	
	Particles >6µm		ASTM D7647		161	389	
	Particles >14µm		ASTM D7647		6	28	
	Particles >21µm		ASTM D7647		1	5	
	Particles >38µm		ASTM D7647		0	0	
	Particles >71µm		ASTM D7647		0	0	
	Oil Cleanliness Silt		ISO 4406 (c)		17/15/10	19/16/12	
	Debris	scalar	*Visual *Visual	NONE	NONE NONE	NONE NONE	
	Sand/Dirt	scalar scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water		*Visual	>0.1	NEG	NEG	
			VISUAI		NLG	INLO	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	0	
	Boron	ppm	ASTM D5185m	5	0	0	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m	5	0	<1	
	Molybdenum	ppm	ASTM D5185m		<1	<1	
	Manganese	ppm	ASTM D5185m		<1	0	
	Magnesium	ppm	ASTM D5185m	25	2	0	
	Calcium	ppm	ASTM D5185m		50	54	
	Phosphorus	ppm	ASTM D5185m	300	357	349	
	Zinc	ppm	ASTM D5185m		436	395	
	Sulfur	ppm	ASTM D5185m	2500	3560	3238	
	Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.28	0.32	
	Visc @ 40°C	cSt	ASTM D445	32	33.7	27.1	
	Visc @ 100°C	cSt	ASTM D445	5.4	6.7	6.7	
	Viscosity Index (VI)	Scale	ASTM D2270	102	160	220	





Certificate L2367

Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0833583 : 06211552

Received **Tested** Unique Number : 11084416 Diagnosed

: 18 Jun 2024 Test Package : MOB 2 (Additional Tests: KV100, VI)

: 17 Jun 2024

: 18 Jun 2024 - Angela Borella To discuss this sample report, contact Customer Service at 1-800-237-1369.

FENTON, MO US 63026 Contact: BRETT HIGGINS brett.higgins@hiab.com T: (636)575-5136

HIAB USA - ST LOUIS

2367 CASSENS DR

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (636)677-5800