WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Machine Id

JOHN DEERE 748L 1DW748LBCPL717838

Rear Differential

JOHN DEERE HY-GARD HYD/TRANS (--- QTS)

JOHN DEERE HY-GARD HYD/TRANS (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WE0007766		
	Sample Date		Client Info		12 Jun 2024		
	Machine Age	hrs	Client Info		489		
	Oil Age	hrs	Client Info		489		
	Filter Age	hrs	Client Info		489		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAD	DO		AOTM D0404				
WEAR	PQ		ASTM D8184	500	32		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		38		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	0.5	0		
	Aluminum	ppm	ASTM D5185m		1		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		7		
	Vanadium	ppm	ASTM D5185m	>10	<1 0		
	White Metal	ppm	ASTM D5185m *Visual	NONE	NONE		
	Yellow Metal	scalar scalar	*Visual	NONE	NONE		
<u></u>		Sudiai	VISUAI	INOINE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	4		
	Water		WC Method	>.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		8		
	Boron	ppm	ASTM D5185m	6	4		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5105m		5		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m	0	4		
	Magnesium	ppm	ASTM D5185m	145	101		
	Calcium	ppm	ASTM D5185m		3588		
	Phosphorus	ppm	ASTM D5185m		1072		
	Zinc	ppm	ASTM D5185m		1241		
	Sulfur	ppm	ASTM D5185m		4262		
	Visc @ 40°C	cSt	ASTM D445	57.0	57.9		
Report Id: WARNOR [WLISCAR] 06212077 (Generated: 06/22/2024 20:22:58) Rev: 1	1100 @ 40 0	001			ation: PAME		WADNO





Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WE0007766 Lab Number : 06212077 Unique Number : 11084941

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received **Tested** Diagnosed

: 17 Jun 2024 : 18 Jun 2024 : 18 Jun 2024 - Wes Davis Test Package : CONST (Additional Tests: PQ)

P.O. BOX 412 NORTHPORT, AL US 35476

Contact: PAMELA CLARK pamela@warriortractor.com T: (205)339-0300

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: