

WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id


24E2903 FS-105

New (Unused) Oil

Fluid

{not provided} (-

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL0005241		
	Sample Date		Client Info		11 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION			40714 05405				
	Silicon	ppm	ASTM D5185m		<1		
	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	NONE	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor Emulsified Water	scalar	*Visual	NORML	NORML		
<u></u>		scalar	visuai		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		<1		
	Calcium	ppm	ASTM D5185m		3		
	Phosphorus	ppm	ASTM D5185m		3		
	Zinc	ppm	ASTM D5185m		1		
	Sulfur	ppm	ASTM D5185m		0		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.041		
	Visc @ 40°C	cSt	ASTM D445		5.27		
		cSt	ASTM D445		1.87		







Certificate L2367

Laboratory Sample No.

: HPL0005241 Lab Number : 06212272 Unique Number : 11085136

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 Jun 2024 **Tested**

: 20 Jun 2024 Diagnosed

: 20 Jun 2024 - Jonathan Hester Test Package : MOB 2 (Additional Tests: FT-IR, KV100, PrtCount, VI)

HIGH PERFORMANCE LUBRICANTS LLC 500 S SPRUCE ST MANTENO, IL US 60950

> Contact: DAVID WARD sampledata@hplubricants.com T: (815)468-3535

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: