



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
MARK DULEY
Machine Id
Component
[MARK DULEY] 004 298357-4
Fluid
CHEVRON MEROPA 320 (150 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0068201	MW0068196	MW0068428
Sample Date		Client Info		03 Jun 2024	01 May 2024	01 Apr 2024
Machine Age	hrs	Client Info		44741	43949	43246
Oil Age	hrs	Client Info		44741	0	43246
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	34	38	35
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	3	2	1
Lead	ppm	ASTM D5185m	>100	<1	1	0
Copper	ppm	ASTM D5185m	>50	38	40	42
Tin	ppm	ASTM D5185m	>10	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	LIGHT	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	4	4	2
Potassium	ppm	ASTM D5185m	>20	6	5	2
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		13	11	12
Boron	ppm	ASTM D5185m	20	15	7	7
Barium	ppm	ASTM D5185m		<1	0	<1
Molybdenum	ppm	ASTM D5185m	0	0	<1	0
Manganese	ppm	ASTM D5185m		1	<1	1
Magnesium	ppm	ASTM D5185m		3	2	0
Calcium	ppm	ASTM D5185m	25	98	36	43
Phosphorus	ppm	ASTM D5185m	235	219	193	203
Zinc	ppm	ASTM D5185m		33	18	12
Sulfur	ppm	ASTM D5185m		9345	8369	9236
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	0.96	0.95	0.97
Visc @ 40°C	cSt	ASTM D445	304	356	353	356



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0068201 **Received** : 17 Jun 2024
Lab Number : 06212535 **Tested** : 19 Jun 2024
Unique Number : 11085399 **Diagnosed** : 19 Jun 2024 - Angela Borella
Test Package : MAR 2

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003

Contact: JUSTIN WHEELER
 justin.wheeler@ingrambarga.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (615)695-3697