



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

DANIEL P MECKLENBORG

Machine Id

[DANIEL P MECKLENBORG] 001 608409-1

Component

Port Main Engine

Fluid

CHEVRON DELO 710 LE (350 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW06212578	MW0065816	MW06148177
Sample Date		Client Info		01 Jun 2024	01 May 2024	01 Apr 2024
Machine Age	hrs	Client Info		64442	63698	63017
Oil Age	hrs	Client Info		0	63698	63017
Filter Age	hrs	Client Info		0	63698	0
Oil Changed		Client Info		N/A	Not Changd	N/A
Filter Changed		Client Info		N/A	None	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	13	15	13
Chromium	ppm	ASTM D5185m	>8	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	<1
Titanium	ppm	ASTM D5185m	>3	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	1	2
Lead	ppm	ASTM D5185m	>18	5	6	6
Copper	ppm	ASTM D5185m	>80	17	17	19
Tin	ppm	ASTM D5185m	>14	3	3	4
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	5	5	7
Potassium	ppm	ASTM D5185m	>20	4	<1	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		1.2	1.3	1.4
Nitration	Abs/cm	*ASTM D7624	>20	8.6	8.6	8.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.5	17.9	18.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	20	16	21
Boron	ppm	ASTM D5185m		40	46	46
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		43	45	49
Manganese	ppm	ASTM D5185m		2	1	1
Magnesium	ppm	ASTM D5185m		15	14	24
Calcium	ppm	ASTM D5185m		3519	3605	3693
Phosphorus	ppm	ASTM D5185m		8	<1	23
Zinc	ppm	ASTM D5185m	10	2	13	17
Sulfur	ppm	ASTM D5185m		2809	2868	2804
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.3	8.4	8.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.2	8.93	8.91	8.51
Visc @ 100°C	cSt	ASTM D445	15.5	14.9	14.9	14.8


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Viscosity @ 100°C




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW06212578

Lab Number : 06212578

Unique Number : 11085442

Test Package : MAR 2

Received : 17 Jun 2024

Tested : 19 Jun 2024

Diagnosed : 19 Jun 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: ANTHONY VAN CURA

anthony.vancura@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)