

WEAR CONTAMINATION FLUID CONDITION

ABNORMAL


NORMAL

Machine Id

CR1206 - 4.2

Component
Right Winch

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		WC0892983		
	Sample Date		Client Info		13 Jun 2024		
	Machine Age	hrs	Client Info		6780		
	Oil Age	hrs	Client Info		682		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				ABNORMAL		
WEAR	Lucia		AOTA DEADE	450	400		
	Iron	ppm	ASTM D5185m		▲ 192		
The iron level is abnormal. All other component wear rates are normal.	Chromium	ppm	ASTM D5185m		2		
	Nickel Titanium	ppm	ASTM D5185m ASTM D5185m	>10	1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	<u> </u>	5		
	Lead	ppm	ASTM D5185m		1		
	Copper	ppm	ASTM D5185m		30		
	Tin	ppm	ASTM D5185m	200	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	4 39		
Elemental level of silicon (Si) above normal indicating ingress of seal material. There is a high amount of visible silt present in the sample.	Potassium	ppm	ASTM D5185m	>20	8		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	▲ HEAVY		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		8		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	50	4		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	15	0		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m	50	2		
	Calcium	ppm	ASTM D5185m	50	18		
	Phosphorus	ppm	ASTM D5185m	350	394		
	Zinc	ppm	ASTM D5185m		38		
	Sulfur	ppm	ASTM D5185m	10500	6384		







Certificate L2367

Laboratory Sample No.

Lab Number : 06212673 Unique Number: 11085537

: WC0892983 Test Package : CONST

195

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 Jun 2024 **Tested** : 19 Jun 2024

Diagnosed : 19 Jun 2024 - Angela Borella

US 27253-9215 Contact: MICHAEL LAWSON michaell@bucknercompanies.com

BUCKNER HEAVY LIFT

4732 NC 54 EAST

GRAHAM, NC

T: (336)376-8888 F: (336)376-4090

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)