WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL


Machine Id


CR1206 - INNER


Rear Right Planetary

GEAR OIL ISO 220 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the	Sample Number		Client Info		WC0923204		
component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Date		Client Info		13 Jun 2024		
	Machine Age	hrs	Client Info		6780		
	Oil Age	hrs	Client Info		682		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	1		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	<1		
	Lead	ppm	ASTM D5185m	>25	0		
	Copper	ppm	ASTM D5185m	>75	<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	0.00		AOTM DEADE	75			
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		<1		
	Potassium	ppm	ASTM D5185m		3		
	Water	cooler	WC Method	>0.2	NEG NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
		scalar	*Visual	NORML	NORML		
	Appearance Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		7		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	15	0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		<1		
	Phosphorus	ppm	ASTM D5185m		425		
	Zinc	ppm		100	4		
	Sulfur	ppm	ASTM D5185m		7329		
	Visc @ 40°C	cSt	ASTM D445	220	218)	











Certificate L2367

Laboratory Sample No.

: WC0923204 Lab Number : 06212689 Unique Number: 11085553 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 Jun 2024 **Tested** : 18 Jun 2024

Diagnosed : 18 Jun 2024 - Wes Davis 4732 NC 54 EAST GRAHAM, NC US 27253-9215

BUCKNER HEAVY LIFT

Contact: MICHAEL LAWSON michaell@bucknercompanies.com

T: (336)376-8888 F: (336)376-4090

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)