



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
441379
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER 15W40 (45 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		IL0033642	IL0030579	IL0026583
Sample Date		Client Info		17 Jun 2024	09 Jan 2024	23 Mar 2023
Machine Age	hrs	Client Info		7813	102794	0
Oil Age	hrs	Client Info		0	83195	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	23	29	28
Chromium	ppm	ASTM D5185m	>20	<1	2	4
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m	>2	0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	13	6	8
Lead	ppm	ASTM D5185m	>40	0	7	5
Copper	ppm	ASTM D5185m	>330	2	2	1
Tin	ppm	ASTM D5185m	>15	0	1	2
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	5	8	9
Potassium	ppm	ASTM D5185m	>20	5	11	15
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.9	0.4	0.4
Nitration	Abs/cm	*ASTM D7624	>20	12.0	10.6	11.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.7	23.1	24.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	0
Boron	ppm	ASTM D5185m	0	4	17	30
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	65	65	50
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m	0	1000	933	565
Calcium	ppm	ASTM D5185m		1159	1209	1870
Phosphorus	ppm	ASTM D5185m		1149	1030	801
Zinc	ppm	ASTM D5185m		1340	1240	1006
Sulfur	ppm	ASTM D5185m		3816	3056	2708
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.9	21.3	26.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.4	8.4	3.8	6.9
Visc @ 100°C	cSt	ASTM D445	14	12.6	12.7	12.7


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : IL0033642

Lab Number : 06212825

Unique Number : 11085689

Test Package : FLEET

Received : 17 Jun 2024

Tested : 19 Jun 2024

Diagnosed : 19 Jun 2024 - Angela Borella

RUSH TRUCK LEASING - CHARLOTTE IDEALEASE

1333 AMERON DR

CHARLOTTE, NC

US 28206

Contact: JERRY DIXON

dixonj@rushenterprises.com

T: (704)333-4507

F: (704)333-4508

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)