WEAR CONTAMINATION FLUID CONDITION


NORMAL ABNORMAL ABNORMAL

Machine Id

723021-361635

Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition.	Sample Number	JOIVI	Client Info	Entity/NOT	GFL0122938	,	GFL011418
	Sample Date		Client Info		12 Jun 2024	10 May 2024	09 Apr 202
	Machine Age	hrs	Client Info		26628	26475	26293
	Oil Age	hrs	Client Info		153	26041	25859
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Changed	Not Change
	Filter Changed		Client Info		Changed	Changed	Not Change
	Sample Status				ABNORMAL	SEVERE	SEVERE
WEAR	Iron	ppm	ASTM D5185m	>100	11	27	23
WEART	Chromium	ppm	ASTM D5185m		<1	2	1
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1	<1	0
	Titanium	ppm	ASTM D5185m		<1	<1	0
	Silver	ppm	ASTM D5185m	>3	<1	<1	0
	Aluminum	ppm	ASTM D5185m		2	4	3
	Lead	ppm	ASTM D5185m		- <1	- <1	0
	Copper	ppm	ASTM D5185m		1	1	4
	Tin	ppm	ASTM D5185m		<1	<1	<1
	Vanadium	ppm	ASTM D5185m		<1	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	> 25	4	8	7
CONTAMINATION	Potassium	ppm	ASTM D5185m		3	7	2
There is a moderate amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.	Fuel	%	ASTM D316311	>5	<u> </u>	, ▲ 19.1	△ 9.4
	Water	, , ,	WC Method		NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	0.4	0.7	0.6
	Nitration	Abs/cm	*ASTM D7624	>20	7.5	10.3	8.9
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1	20.4	19.0
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		28	50	41
	Boron	ppm	ASTM D5185m	0	5	0	3
The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.	Barium	ppm	ASTM D5185m		<1	0	<1
	Molybdenum	ppm	ASTM D5185m		52	47	54
	Manganese	ppm	ASTM D5185m		<1	<1	2
	Magnesium	ppm	ASTM D5185m		822	695	853
	Calcium	ppm	ASTM D5185m		974	848	1004
	Phosphorus	ppm	ASTM D5185m	1150	955	837	951
	Zinc	ppm	ASTM D5185m	1270	1099	989	1116
	Sulfur	ppm	ASTM D5185m	2060	2909	2652	3002
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	19.1	15.5
		110111	A OTH A DOGGO	0.0	0.4	0.0	7.0
	Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.1	6.2	7.9







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0122938 Lab Number : 06212967

Unique Number : 11085831

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Test Package: FLEET (Additional Tests: PercentFuel)

Received : 17 Jun 2024 **Tested** Diagnosed

: 20 Jun 2024 : 20 Jun 2024 - Wes Davis

GFL Environmental - 837 - Harrison TS 22820 S State Route 291 Harrisonville, MO

US 64701 Contact: SARA PATRICK

spatrick@gflenv.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: