



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
2619C
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (12 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0079616	GFL0112919	GFL0098151
Sample Date		Client Info		18 Jun 2024	07 May 2024	13 Feb 2024
Machine Age	hrs	Client Info		10382	10382	10382
Oil Age	hrs	Client Info		150	550	399
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	4	4	4
Chromium	ppm	ASTM D5185m	>4	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>9	2	<1	1
Lead	ppm	ASTM D5185m	>30	<1	<1	<1
Copper	ppm	ASTM D5185m	>35	<1	0	<1
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	6	6	12
Potassium	ppm	ASTM D5185m	>20	14	1	5
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	8.5	10.0	9.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.9	20.9	20.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	5	8
Boron	ppm	ASTM D5185m	50	23	13	16
Barium	ppm	ASTM D5185m	5	<1	<1	0
Molybdenum	ppm	ASTM D5185m	50	51	51	52
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	560	546	553	616
Calcium	ppm	ASTM D5185m	1510	1493	1621	1634
Phosphorus	ppm	ASTM D5185m	780	705	716	713
Zinc	ppm	ASTM D5185m	870	927	948	1014
Sulfur	ppm	ASTM D5185m	2040	2446	2870	2622
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.7	18.2	17.5
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	7.3	5.0	5.6
Visc @ 100°C	cSt	ASTM D445	15.1	14.8	13.3	14.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0079616
Lab Number : 06213139
Unique Number : 11086003
Test Package : FLEET

GFL Environmental - 017 - Durham
 148 Stone Park Court
 Durham, NC
 US 27703
 Contact:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

bill.waring@wearcheck.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (919)596-1363

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (919)598-1852