



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[W52399]

Machine Id

JOHN DEERE 1DW624PAJMLT10737

Component

Hydraulic System

Fluid

JOHN DEERE HYDRAU (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0211780	JR0125560	JR0148113
Sample Date		Client Info		11 Jun 2024	30 Jun 2023	18 Jan 2023
Machine Age	hrs	Client Info		1940	1455	956
Oil Age	hrs	Client Info		0	1455	956
Filter Age	hrs	Client Info		0	1455	956
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Test	UOM	Method	Limit/Abn	Current	History1	History2
PQ		ASTM D8184		20	9	9
Iron	ppm	ASTM D5185m	>20	3	2	2
Chromium	ppm	ASTM D5185m	>10	3	2	2
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		<1	0	<1
Aluminum	ppm	ASTM D5185m	>10	2	0	<1
Lead	ppm	ASTM D5185m	>10	1	0	<1
Copper	ppm	ASTM D5185m	>75	2	1	1
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	2	<1	<1
Potassium	ppm	ASTM D5185m	>20	6	5	6
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>5000	2066	1003	1320
Particles >6µm		ASTM D7647	>1300	179	128	242
Particles >14µm		ASTM D7647	>160	14	12	14
Particles >21µm		ASTM D7647	>40	3	5	3
Particles >38µm		ASTM D7647	>10	0	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	18/15/11	17/14/11	18/15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	0	1
Molybdenum	ppm	ASTM D5185m		<1	0	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		1	<1	3
Calcium	ppm	ASTM D5185m	87	77	90	97
Phosphorus	ppm	ASTM D5185m	727	558	651	612
Zinc	ppm	ASTM D5185m	900	817	883	842
Sulfur	ppm	ASTM D5185m	1500	1574	2020	1645
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.50	0.56	0.61
Visc @ 40°C	cSt	ASTM D445	65	60.1	59.8	60.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : JR0211780 Received : 18 Jun 2024
 Lab Number : 06213382 Tested : 19 Jun 2024
 Unique Number : 11086246 Diagnosed : 19 Jun 2024 - Wes Davis
 Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

HENDERSON INC
 5806 MOORETOWN RD
 WILLIAMSBURG, VA
 US 23188
 Contact: TERRY THOMPSON
 terry@hendersoninc.com
 T: (757)603-0418
 F: