**WEAR CONTAMINATION FLUID CONDITION**  **ATTENTION ABNORMAL NORMAL** 

Machine Id

## **JOHN DEERE 350G 1FF350GXPKF814095**

**Left Final Drive** 


JOHN DEERE GL-5 80W90 (5 QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		JR0222266	JR0197457	JR015650
	Sample Date		Client Info		13 Jun 2024	05 Dec 2023	20 Dec 202
	Machine Age	hrs	Client Info		6191	5759	4355
	Oil Age	hrs	Client Info		4787	1404	0
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Not Changd	Changed
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				ABNORMAL	ABNORMAL	SEVERE
WEAR	PQ		ASTM D8184	>1250	315	335	672
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	970	836	<b>1</b> 986
	Chromium	ppm	ASTM D5185m	>9	6	6	<u> </u>
	Nickel	ppm	ASTM D5185m	>10	<1	<1	3
	Titanium	ppm	ASTM D5185m		3	3	9
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m	>40	<b>23</b>	<u>21</u>	57
	Lead	ppm	ASTM D5185m		0	0	0
	Copper	ppm	ASTM D5185m		2	2	4
	Tin	ppm	ASTM D5185m	>10	0	0	0
	Vanadium	ppm	ASTM D5185m		<1	0	<1
	White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	<b>136</b>	<b>▲</b> 112	<b>261</b>
Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress.	Potassium	ppm	ASTM D5185m	>20	1	2	2
	Water		WC Method	>0.075	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
·····	Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2	3	4
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		2	4	17
	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		0	0	2
	Manganese	ppm	ASTM D5185m		8	7	17
	Magnesium	ppm	ASTM D5185m		1	0	14
	Calcium	ppm	ASTM D5185m		60	14	49
	Phosphorus	ppm	ASTM D5185m		2193	2200	1995
	Zinc	ppm	ASTM D5185m		22	8	40
	Sulfur	ppm	ASTM D5185m		27999	25182	24161
	V" 0 4000	- 04	AOTA DA45		470	407	470

Visc @ 40°C cSt

ASTM D445

187

Submitted By: Jeffrey Moore





Certificate L2367

Laboratory Sample No. Lab Number

: 06213700

: JR0222266 Unique Number : 11086564

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received Tested Diagnosed

: 18 Jun 2024 : 20 Jun 2024

: 20 Jun 2024 - Sean Felton

JRE - GREENVILLE 3604 HIGHWAY 264 E GREENVILLE, NC US 27834-5800 Contact: GREENVILLE SHOP

Test Package : CONST ( Additional Tests: PQ ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

christopher.martin@jamesriverequipment.com T:

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: