

# [W52559] JOHN DEERE 333E 1T0333EMCGE298722

### Left Final Drive

JOHN DEERE GL-5 80W90 (--- GAL)

### RECOMMENDATION

We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.

#### WEAR

Gear wear is indicated.

## CONTAMINATION

Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress. The water content is negligible.

Test	UOM	Method	Limit/Abn	Cı	urrent	History1	History2
Sample Number		Client Info		JF	0211769		
Sample Date		Client Info		14	Jun 2024		
Machine Age	hrs	Client Info		20	36		
Oil Age	hrs	Client Info		10	00		
Filter Age	hrs	Client Info		0			
Oil Changed		Client Info		CI	nanged		
Filter Changed		Client Info		N/	Ά		
Sample Status				SE	EVERE		
PO		4STM D8184	<1250		235		
Iron	nnm	ASTM D5185m	>750		3580		
Chromium	nom	ASTM D5185m	>9		32		
Nickel	npm	ASTM D5185m	>10		16		
Titanium	nom	ASTM D5185m	210		9		
Silver	ppm	ASTM D5185m			0		
Aluminum	mag	ASTM D5185m	>40		- 125		
Lead	mag	ASTM D5185m	>15		0		
Copper	mag	ASTM D5185m	>40		4		
Tin	ppm	ASTM D5185m	>10		0		
Vanadium	ppm	ASTM D5185m			2		
White Metal	scalar	*Visual	NONE		NONE		
Yellow Metal	scalar	*Visual	NONE		NONE		
Silicon	ppm	ASTM D5185m	>75		495		
Potassium	ppm	ASTM D5185m	>20		26		
Water	%	ASTM D6304	>0.075		0.188		
ppm Water	ppm	ASTM D6304	>750		1880		
Silt	scalar	*Visual	NONE		NONE		
Debris	scalar	*Visual	NONE		NONE		
Sand/Dirt	scalar	*Visual	NONE		NONE		
Appearance	scalar	*Visual	NORML		NORML		
Odor	scalar	*Visual	NORML		NORML		
Emulsified Water	scalar	^Visual	>0.075		0.2%		
Sodium	ppm	ASTM D5185m	>51		15		
Boron	ppm	ASTM D5185m			10		
Barium	ppm	ASTM D5185m			4		
Molybdenum	ppm	ASTM D5185m			5		
Manganese	ppm	ASTM D5185m			26		
Magnesium	ppm	ASTM D5185m			12		
Calcium	ppm	ASTM D5185m			55		
Phosphorus	ppm	ASTM D5185m			2128		
Zinc	ppm	ASTM D5185m			45		
Sulfur	ppm	ASTM D5185m			29796		
Visc @ 40°C	cSt	ASTM D445			173		

### **FLUID CONDITION**

The oil is no longer serviceable due to the presence of contaminants.

Contact/Location: DAVID ZIEG - JAMASH



JRE - ASHLAND Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received 11047 LEADBETTER RD : JR0211769 : 18 Jun 2024 Lab Number : 06213704 Tested : 20 Jun 2024 ASHLAND, VA Unique Number : 11086568 : 20 Jun 2024 - Sean Felton US 23005 Diagnosed Test Package : CONST (Additional Tests: KF, PQ) Contact: DAVID ZIEG Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. dzieg@jamesriverequipment.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (804)798-6001 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (804)798-0292

Contact/Location: DAVID ZIEG - JAMASH Page 2 of 2