

WEAR
CONTAMINATION
FLUID CONDITION

ABNORMAL SEVERE NORMAL




Store 6 - Ashland [152020]

JOHN DEERE 325G 1T0325GKTLJ371424

Right Propel Gearbox

JOHN DEERE GL-5 80W90 (27	Oz)				-		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition.	Sample Number		Client Info		LEC0044657		
	Sample Date		Client Info		14 Jun 2024		
	Machine Age	hrs	Client Info		773		
	Oil Age	hrs	Client Info		773		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				SEVERE		
WEAR	PQ		ASTM D8184		207		
Gear wear is indicated.	Iron	ppm	ASTM D5185m	>1250	<u> </u>		
	Chromium	ppm	ASTM D5185m	>10	<u> </u>		
	Nickel	ppm	ASTM D5185m	>10	<u> </u>		
	Titanium	ppm	ASTM D5185m		5		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<u>66</u>		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		6		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress.	Silicon	ppm	ASTM D5185m		▲ 252		
	Potassium	ppm	ASTM D5185m		43		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual *Visual	NONE	NONE NORML		
	Appearance Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
			• • • • • • • • • • • • • • • • • • •				
FLUID CONDITION	Sodium	ppm	ASTM D5185m		7		
The oil is no longer serviceable due to the presence of contaminants.	Boron	ppm	ASTM D5185m		37		
	Barium	ppm	ASTM D5185m		23		
	Molybdenum	ppm	ASTM D5185m		3		
	Manganese	ppm	ASTM D5185m		18		
	Magnesium	ppm	ASTM D5185m		15		
	Calcium	ppm	ASTM D5185m		94		
	Phosphorus	ppm	ASTM D5185m		345		
	Zinc	ppm	ASTM D5185m		77		
	Sulfur	ppm	ASTM D5185m		15652		
Danast Id. L FCMADOLL (AULICOAD) 00010705 (Consented) 00(01/0004 10:05:00) Days 1	Visc @ 40°C	cSt	ASTM D445	TODE	136		





Laboratory Sample No.

Lab Number : 06213765

Unique Number : 11086629

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : LEC0044657 **Tested**

Diagnosed Test Package : CONST (Additional Tests: PQ)

: 20 Jun 2024 : 20 Jun 2024 - Sean Felton

: 18 Jun 2024

Contact: LEANNE KENDALL KendalLeanne@lec1.com

LESLIE EQUIPMENT COMPANY

T:

105 TENNIS CENTER DR.

MARIETTA, OH

US 45750-9765

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (740)373-5570