

**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 


**Erickson Metals**Machine Id

149789 Component

Diesel Engine

SHELL 15W40 (32 GAL)

SHELL 15W40 (32 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TEOGRAMETON	Sample Number		Client Info		RPL0021222		
Resample at the next service interval to monitor.	Sample Date		Client Info		11 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		12		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	<1		
	Nickel	ppm	ASTM D5185m	>4	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m	>20	4		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon		ASTM D5185m	. 05	4		
CONTAMINATION	Potassium	ppm	ASTM D5185m		4		
There is no indication of any contamination in the oil.	Fuel	ppm	WC Method				
	Water				<1.0 NEG		
			WC Method WC Method	>0.2	NEG		
	Glycol Soot %	%	*ASTM D7844	. 2	0.3		
	Nitration	Abs/cm	*ASTM D7644	>20	9.3		
	Sulfation	Abs/.1mm			19.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
	Linuisinca Water		Visuai				
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>150	3		
	Boron	ppm	ASTM D5185m		76		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		100		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		721		
	Calcium	ppm	ASTM D5185m		1257		
	Phosphorus	ppm	ASTM D5185m		799		
	Zinc	ppm	ASTM D5185m		923		
	Sulfur	ppm	ASTM D5185m		3578		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	16.3		
	Base Number (BN)	mg KOH/g	ASTM D2896		7.0		
	Visc @ 100°C	cSt	ASTM D445		13.0		







Certificate L2367

Laboratory Sample No.

Lab Number : 06214380 Unique Number : 11087244 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : RPL0021222 : 19 Jun 2024 **Tested** : 20 Jun 2024

Diagnosed : 21 Jun 2024 - Don Baldridge

3500 Doniphan Dr El Paso, TX US 79922

Contact: JUAN MARTINEZ martinezj15@rushenterprises.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: