



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
Mobile Fleet
 Machine Id
8037 8037
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0947765	WC0939412	WC0918667
Sample Date		Client Info		17 Jun 2024	09 May 2024	27 Mar 2024
Machine Age	hrs	Client Info		6274	5954	5668
Oil Age	hrs	Client Info		320	612	326
Filter Age	hrs	Client Info		320	612	326
Oil Changed		Client Info		Not Chngd	Changed	Not Chngd
Filter Changed		Client Info		Not Chngd	Changed	Not Chngd
Sample Status				NORMAL	ATTENTION	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	4	10	7
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	4	4	3
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	2	5	5
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION


The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	5	7
Potassium	ppm	ASTM D5185m	>20	8	4	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.4	0.2
Nitration	Abs/cm	*ASTM D7624	>20	7.2	8.4	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	21.8	21.9
Particles >4µm		ASTM D7647	>20000	4907	9265	1879
Particles >6µm		ASTM D7647	>5000	2673	5047	1024
Particles >14µm		ASTM D7647	>640	455	859	174
Particles >21µm		ASTM D7647	>160	153	289	59
Particles >38µm		ASTM D7647	>40	24	45	9
Particles >71µm		ASTM D7647	>10	2	5	1
Oil Cleanliness		ISO 4406 (c)	>21/19/16	19/19/16	20/20/17	18/17/15
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	1	<1
Boron	ppm	ASTM D5185m		35	25	47
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		44	46	48
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		521	546	515
Calcium	ppm	ASTM D5185m		1661	1857	1737
Phosphorus	ppm	ASTM D5185m		793	786	696
Zinc	ppm	ASTM D5185m		937	985	942
Sulfur	ppm	ASTM D5185m		2918	2889	2630
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.6	21.1	20.4
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	9.1	8.6	9.8
Visc @ 100°C	cSt	ASTM D445	11.9	11.3	11.7	11.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0947765 **Received** : 19 Jun 2024
Lab Number : 06214505 **Tested** : 20 Jun 2024
Unique Number : 11087369 **Diagnosed** : 21 Jun 2024 - Don Baldrige

CAROLINA SUNROCK
 PO BOX 25
 BUTNER, NC
 US 27509
 Contact: Leigh Dennis
 rdennis@thesunrockgroup.com
 T: (919)575-4505
 F: (919)575-0162

Test Package : CONST (Additional Tests: PrtCount, TBN)
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)