WEAR
CONTAMINATION
FLUID CONDITION


NORMAL NORMAL NORMAL

FOOD GRADE 32

ATLAS COPCO WUX584999 - NU-TEK

Compressor

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		UCS06214819		
	Sample Date		Client Info		11 Jun 2024		
	Machine Age	hrs	Client Info		32685		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>50	0		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>5	0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>15	0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		6		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		<1		
Moderate concentration of visible dirt/debris present in the oil.	Potassium	ppm	ASTM D5185m		3		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	MODER		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m	1	0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	0	0		
	Manganese	ppm	ASTM D5185m	0	<1		
	Magnesium	ppm	ASTM D5185m	0	0		
	Calcium	ppm	ASTM D5185m	0.5	0		
	Phosphorus	ppm	ASTM D5185m	536	410		
	Zinc	ppm	ASTM D5185m		13		
	Sulfur	ppm	ASTM D5185m	649	1279		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.50		
	Visc @ 40°C	cSt	ASTM D445		42.1		







Certificate L2367

Laboratory Sample No.

Lab Number : 06214819 Unique Number : 11087683

: UCS06214819

Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Jun 2024

Tested Diagnosed

: 20 Jun 2024 : 21 Jun 2024 - Sean Felton

0.00

JEMCO-MAXAIR WEST FARGO, ND

US 58078 Contact: DALE K dalek@jemco-maxair.com

T: (701)281-0362 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)