**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 



## Machine Id **JOHN DEERE 300D 1DW300DXCFE672711**

Front Front Left Final Drive

{not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the	Sample Number		Client Info		JR0220486		
brand, type, and viscosity of the oil on your next sample.	Sample Date		Client Info		17 Jun 2024		
	Machine Age	hrs	Client Info		9135		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	40		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	102		
	Chromium	ppm	ASTM D5185m	>9	<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	2		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	30		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	8		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		61		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		23		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		5		
	Calcium	ppm	ASTM D5185m		1906		
	Phosphorus	ppm	ASTM D5185m		1464		
	Zinc	ppm	ASTM D5185m		756		
	Sulfur	ppm	ASTM D5185m		21709		
	Visc @ 40°C	cSt	ASTM D445		286		 huck Sorrow





Report Id: JAMCHA [WUSCAR] 06214990 (Generated: 06/23/2024 03:56:32) Rev: 1

Laboratory Sample No.

: JR0220486 Lab Number : 06214990

Unique Number : 11087854

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Jun 2024 **Tested** 

Diagnosed Test Package : CONST ( Additional Tests: PQ )

: 20 Jun 2024 : 21 Jun 2024 - Sean Felton

JRE - CHARLOTTE 9550 STATESVILLE ROAD CHARLOTTE, NC US 28269

Contact: Chuck Sorrow

To discuss this sample report, contact Customer Service at 1-800-237-1369. JSorrow@jamesriverequipment.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (704)596-6198

Submitted By: Chuck Sorrow