WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

Machine Id

JOHN DEERE 300D 1DW300DXCFE672711

Front Differential

GEAR OIL SAF 80W90 (--- GAL)

GEAR OIL SAE 80W90 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		JR0220455		
	Sample Date		Client Info		17 Jun 2024		
	Machine Age	hrs	Client Info		9135		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAD	DO.		ACTM DO104		00		
WEAR	PQ		ASTM D8184	F00	22		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		112		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m ASTM D5185m	> 2F	2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	>10	<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	1		
	Water		WC Method	>.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		37		
	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m		7		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m	12	0		
	Calcium	ppm	ASTM D5185m		30		
	Phosphorus	ppm	ASTM D5185m	1650	1028		
	Zinc	ppm	ASTM D5185m	125	22		
	Sulfur	ppm	ASTM D5185m	22500	20750		
	Visc @ 40°C	cSt	ASTM D445		179		
Report Id: JAMCHA [WUSCAR] 06215003 (Generated: 06/23/2024 03:02:42) Rev: 1					Subn	nitted By: Cl	nuck Sorrow







Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No.

: JR0220455 Lab Number : 06215003 Unique Number : 11087867

Tested Diagnosed Test Package : CONST (Additional Tests: PQ)

Received : 19 Jun 2024 : 20 Jun 2024

: 20 Jun 2024 - Wes Davis

JRE - CHARLOTTE 9550 STATESVILLE ROAD CHARLOTTE, NC

US 28269 Contact: Chuck Sorrow

To discuss this sample report, contact Customer Service at 1-800-237-1369.

JSorrow@jamesriverequipment.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (704)596-6198