WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL


Machine Id


31269


Left Final Drive

RECOMMENDATION	Toot	LIONA	Mothad	Limit/Abs	Current	Lliotomid	Lintary
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0913583		
	Sample Date Machine Age	hrs	Client Info		10 Jun 2024 470		
	Oil Age		Client Info		500		
	Filter Age	hrs	Client Info		500		
	Oil Changed	1113	Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	67		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NONE	<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	9		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium		ACTM DE10Em	. 170			
	Boron	ppm	ASTM D5185m ASTM D5185m		7		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		6		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m	14	1		
	Magnesium	ppm	ASTM D5185m	12	0		
	Calcium	ppm	ASTM D5185m		14		
	Phosphorus	ppm	ASTM D5185m		1178		
	Zinc	ppm	ASTM D5185m		16		
	Sulfur	ppm	ASTM D5185m		28468		
	Visc @ 40°C	cSt	ASTM D445		198		











Certificate L2367

Report Id: MSCDUR [WUSCAR] 06215031 (Generated: 06/23/2024 03:05:54) Rev: 1

Laboratory Sample No.

: WC0913583 Lab Number : 06215031 Unique Number : 11087895 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Jun 2024 **Tested** : 20 Jun 2024

> Diagnosed : 20 Jun 2024 - Wes Davis

SULLIVAN EASTERN INC

2860 C SLATER RD MORRISVILLE, NC US 27560

Contact: SCOTT SULLIVAN ssullivan@sullivaneastern.com

T: (919)484-8993 F: (919)484-2136

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)