

Machine Id

VOLVO A40G 353294 ponent **Front Axle**



| | | | | | ~~~~~ | | |
|---|------------------|--------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | VCP436734 | | |
| | Sample Date | | Client Info | | 15 Jun 2024 | | |
| | Machine Age | hrs | Client Info | | 2575 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | Changed | | |
| | Sample Status | | | | ATTENTION | | |
| | | | | | | | |
| WEAR | Iron | ppm | ASTM D5185m | | 363 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | >20 | 4 | | |
| | Nickel | ppm | ASTM D5185m | >10 | 2 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >30 | 2 | | |
| | Lead | ppm | ASTM D5185m | >50 | <1 | | |
| | Copper | ppm | ASTM D5185m | >150 | 4 | | |
| | Tin | ppm | ASTM D5185m | >20 | 0 | | |
| | Vanadium | ppm | ASTM D5185m | | 0 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | | | | | _ | | |
| | Silicon | ppm | ASTM D5185m | | 5 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | | 5 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 2 | | |
| | Boron | ppm | ASTM D5185m | 111 | 197 | | |
| The oil viscosity is lower than normal. Confirm oil type. | Barium | ppm | ASTM D5185m | | 1 | | |
| | Molybdenum | ppm | ASTM D5185m | | 4 | | |
| | Manganese | ppm | ASTM D5185m | | 15 | | |
| | Magnesium | ppm | ASTM D5185m | | 2 | | |
| | Calcium | ppm | ASTM D5185m | | - 12 | | |
| | Phosphorus | ppm | ASTM D5185m | | 2329 | | |
| | Zinc | ppm | ASTM D5185m | | 21 | | |
| | Sulfur | ppm | ASTM D5185m | | 26853 | | |
| | Juliu | PPIII | | 20175 | 20000 | | |


Visc @ 40°C


cSt

Contact/Location: TODD LARK - VOLVO0090

50.8

ASTM D445 333







ALTA EQUIPMENT COMPANY Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received 5151 DR MARTIN LUTHER KING BLVD : VCP436734 : 19 Jun 2024 Lab Number : 06215118 Tested : 20 Jun 2024 FORT MYERS, FL Diagnosed Unique Number : 11087982 : 21 Jun 2024 - Sean Felton US 33905 Test Package : MOB 1 Contact: TODD LARK Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tlark@altaequipfl.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Т: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (239)481-3302

Contact/Location: TODD LARK - VOLVO0090 Page 2 of 2