**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL ATTENTION** 

## [581211]

## **VOLVO A25G 752693**



DECOMMENDATION	Toot	LIONA	Mothad	Limit/Aba	Current	Lintond	Llioton:0
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Test	UOM	Method	Limit/Abn	Current VCP449593	History1	History2
	Sample Number Sample Date		Client Info		19 Jun 2024		
	Machine Age	hrs	Client Info		971		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1115	Client Info				
					Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				ATTENTION		
VEAR	Iron	ppm	ASTM D5185m	>100	28		
	Chromium	ppm	ASTM D5185m		<1		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185m		3		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	<b>\2</b>	<1		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m	>40	<1 <1		
	Copper	ppm	ASTM D5185m		218		
	Tin	ppm	ASTM D5185m		3		
	Vanadium	ppm	ASTM D5185m	>10	<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal		*Visual	NONE	NONE		
		scalar	Visuai	NONL	INOINE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	39		
Fuel content negligible. There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		6		
	Fuel	%	ASTM D3524	>6.0	0.4		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.4		
	Nitration	Abs/cm	*ASTM D7624	>20	10.2		
	Sulfation	Abs/.1mm	*ASTM D7415		22.3		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		6		
	Boron	ppm	ASTM D5185m	2.5	30		
The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		91		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m		84		
	Calcium	ppm	ASTM D5185m	2057	2216		
	Phosphorus	ppm	ASTM D5185m		1027		
	Zinc	ppm		1223	1224		
	Sulfur	ppm	ASTM D5185m		4147		
	Oxidation	Abs/.1mm	*ASTM D7414		16.1		
	Base Number (BN)		ASTM D2896		5.2		





Laboratory Sample No. Unique Number : 11088276

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : VCP449593 Lab Number : 06215412

Received : 20 Jun 2024 **Tested** Diagnosed

: 24 Jun 2024 : 24 Jun 2024 - Jonathan Hester

ALTA EQUIPMENT/FLAGLER EQUIPMENT LLC 9601 BOGGY CREEK RD

ORLANDO, FL US 32824 Contact: JUSTIN KENNEDY

Test Package: MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JUSTIN.KENNEDY@ALTG.COM T: F: (407)659-8720