



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 748L 1dw748lbep1717202

Component
Hydraulic System

Fluid
{not provided} (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0222026	JR0209670	JR0164603
Sample Date		Client Info		18 Jun 2024	17 Apr 2024	23 Jan 2024
Machine Age	hrs	Client Info		2493	2128	1587
Oil Age	hrs	Client Info		0	0	1587
Filter Age	hrs	Client Info		0	0	1587
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ	UOM	Method	Limit/Abn	Current	History1	History2
Iron	ppm	ASTM D5185m	>20	5	5	5
Chromium	ppm	ASTM D5185m	>10	4	3	3
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	<1	<1	0
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	1	2	3
Tin	ppm	ASTM D5185m	>10	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	5	5	4
Potassium	ppm	ASTM D5185m	>20	5	5	0
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>5000	625	1312	1242
Particles >6µm		ASTM D7647	>1300	128	164	200
Particles >14µm		ASTM D7647	>160	10	16	13
Particles >21µm		ASTM D7647	>40	2	4	5
Particles >38µm		ASTM D7647	>10	0	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	16/14/10	18/15/11	17/15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	2	2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		2	3	0
Calcium	ppm	ASTM D5185m		87	87	87
Phosphorus	ppm	ASTM D5185m		677	651	641
Zinc	ppm	ASTM D5185m		870	836	769
Sulfur	ppm	ASTM D5185m		1938	1940	1628
Acid Number (AN)	mg KOH/g	ASTM D8045		0.68	0.78	0.69
Visc @ 40°C	cSt	ASTM D445		56.0	56.6	57.4



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0222026 **Received** : 20 Jun 2024
Lab Number : 06215714 **Tested** : 21 Jun 2024
Unique Number : 11088578 **Diagnosed** : 21 Jun 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

NEUSE RIVER FOREST PRODUCTS
 PO BOX 234
 PRINCETON, NC
 US 27569
 Contact: Service Manager
 neuseriverftp@gmail.com
 T:
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)