
WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**



Machine Id JENBACHER GM03 (S/N 1144731) Component Biogas Engine

MAHLER Q8 Mahler G8 SAE 40 (--- GAL)

MARLER Q8 Manier G8 SAE 40	(GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
RESOMMENDATION	Sample Number	OOW	Client Info	LITTIOTION	WC0914302	WC0914299	WC0914298
Resample at the next service interval to monitor.	Sample Date		Client Info		18 Jun 2024	10 Jun 2024	03 Jun 2024
	Machine Age	hrs	Client Info		52285	52124	51962
	Oil Age	hrs	Client Info		665	525	363
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m	>20	6	7	6
	Chromium	ppm	ASTM D5185m	>5	0	<1	0
	Nickel	ppm	ASTM D5185m	>2	0	0	0
	Titanium	ppm	ASTM D5185m		0	<1	0
	Silver	ppm	ASTM D5185m	>5	0	0	0
	Aluminum	ppm	ASTM D5185m	>15	2	2	2
	Lead	ppm	ASTM D5185m		0	0	0
	Copper	ppm	ASTM D5185m		<1	1	<1
	Tin	ppm	ASTM D5185m	>5	1	2	<1
	Vanadium	ppm	ASTM D5185m	NONE	0	0	<1
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>200	16	16	13
	Potassium	ppm	ASTM D5185m	>20	0	2	0
There is no indication of any contamination in the oil.	Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
	Water		WC Method	>.2	NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>2	0	0	0
	Nitration	Abs/cm	*ASTM D7624	>20	7.2	7.1	6.7
	Sulfation	Abs/.1mm	*ASTM D7415		16.1	15.9	15.4
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance Odor	scalar scalar	*Visual *Visual	NORML NORML	NORML NORML	NORML NORML	NORML NORML
	Emulsified Water		*Visual	>.2	NEG	NEG	NEG
	Liliuisilleu vvalei	Scalai	Visuai	>.८	NEG	INLG	INLG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>20	1	0	2
	Boron	ppm	ASTM D5185m		0	0	0
The BN result indicates that there is suitable alkalinity remaining in the	Barium	ppm	ASTM D5185m		0	0	0
oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Molybdenum	ppm	ASTM D5185m		0	<1	0
Culture for further service.	Manganese	ppm	ASTM D5185m		<1	<1	<1
	Magnesium	ppm	ASTM D5185m		5	6	0
	Calcium	ppm	ASTM D5185m		2314	2334	2449
	Phosphorus	ppm	ASTM D5185m		382	398	415
	Zinc	ppm	ASTM D5185m		433	475	451
	Sulfur	ppm Abo/ 1mm	ASTM D5185m	- OF	2708	2863	2742
	Oxidation Acid Number (AN)	Abs/.1mm	*ASTM D7414 ASTM D8045	>20	11.7	11.3	10.8
	Base Number (BN)	mg KOH/g		8.0	0.63 6.79	0.53 6.97	1.509 6.78
	Visc @ 100°C		ASTM D2696 ASTM D445		13.8	13.1	13.6
	VISC W 100 C	COL	AOTIVI D443	10.2	13.6	10.1	10.0





Certificate L2367

Laboratory Sample No.

: WC0914302 Lab Number : 06215916 Unique Number : 11088780 Test Package : MOB 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** Diagnosed

: 20 Jun 2024 : 22 Jun 2024 : 23 Jun 2024 - Don Baldridge

PINE RIDGE 105 BAILEY JESTER RD GRIFFIN, GA

US 30224 Contact: STEPHEN SAVAGE

To discuss this sample report, contact Customer Service at 1-800-237-1369.

stephen.savage@cubedistrictenergy.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: