



**WEAR CONTAMINATION FLUID CONDITION** 

**NORMAL ABNORMAL NORMAL** 



Machine Id JOHN DEERE 650K 1T0650KKLNF418076

Rear Right Final Drive							
{not provided} ( GAL)							
RECOMMENDATION	Test	LIOM	Mothod	Limit/Alan	O	Lliotomid	LliatoryO
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number	UOM	Method Client Info	Limit/Abn	Current LEC0048687	History1	History2
	Sample Date		Client Info		20 Jun 2024		
	Machine Age	hro	Client Info		501		
	Oil Age	hrs hrs	Client Info		501		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1113	Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status		Olicit iiilo		ABNORMAL		
WEAR All component wear rates are normal.	PQ		ASTM D8184		36		
	Iron	ppm	ASTM D5185m		50		
	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	40	0		
	Aluminum	ppm	ASTM D5185m		1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NIONIE	0		
	White Metal Yellow Metal	scalar	*Visual  *Visual	NONE	NONE NONE		
		scalar	VISUAI		NONE		
CONTAMINATION  There is a light concentration of water present in the oil.	Silicon	ppm	ASTM D5185m	>75	8		
	Potassium	ppm	ASTM D5185m	>20	7		
	Water	%	ASTM D6304	>0.075	<b>△</b> 0.273		
	ppm Water	ppm	ASTM D6304	>750	<u> </u>		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	0.2%		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	5		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		2		
	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		96		
	Calcium	ppm	ASTM D5185m		3346		
	Phosphorus	ppm	ASTM D5185m		1063		
	Zinc	ppm	ASTM D5185m		1233		
	0.16		1071107107				

Sulfur

Visc @ 40°C

ppm

ASTM D5185m

4385

53.4





Laboratory

Sample No.

Lab Number : 06215986

: LEC0048687 Unique Number : 11088850

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

: 20 Jun 2024 : 22 Jun 2024 Diagnosed

Test Package : CONST ( Additional Tests: KF, PQ )

: 23 Jun 2024 - Don Baldridge Contact: Service Manager arnettsexcavation@yahoo.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

US 41465

ARNETTS EXCAVATION

462 MILL BRANCH RD

SALYERSVILLE, KY

T: (606)496-6400