

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Store 1 - Cowen [RO#151463]

## JOHN DEERE 260P 1DW260PAHPFB06710

**Rear Axle** 

JOHN DEERE HY-GARD HYD/TRANS (10 GAL)

JOHN DEERE HY-GARD HYD/TRANS (10 GAL)	) 						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0051210	LEC0043508	
	Sample Date		Client Info		18 Jun 2024	13 Oct 2023	
	Machine Age	hrs	Client Info		1110	661	
	Oil Age	hrs	Client Info		1110	661	
	Filter Age	hrs	Client Info		1110	661	
	Oil Changed		Client Info		Not Changd	Not Changd	
	Filter Changed		Client Info		Not Changd	Not Changd	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184		42	106	
	Iron	ppm	ASTM D5185m	>1501	57	162	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	2	
	Nickel	ppm	ASTM D5185m		1	6	
	Titanium	ppm	ASTM D5185m		0	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>21	2	4	
	Lead	ppm	ASTM D5185m		- <1	0	
	Copper	ppm	ASTM D5185m		27	59	
	Tin	ppm	ASTM D5185m	>10	1	4	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	0:1:		AOTA D5405	04		4.4	
CONTAMINATION	Silicon	ppm	ASTM D5185m		8	14	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0	<1	
	Water		WC Method		NEG	NEG	
	Silt Debris	scalar	*Visual	NONE	NONE	NONE NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE NONE	NONE	
		scalar	*Visual	NORML	NORML	NORML	
	Appearance Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
			····				
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	6	20	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	16	117	
	Barium	ppm	ASTM D5185m	0	<1	0	
	Molybdenum	ppm	ASTM D5185m	0	5	0	
	Manganese	ppm	ASTM D5185m		13	38	
	Magnesium	ppm	ASTM D5185m	145	108	8	
	Calcium	ppm	ASTM D5185m	3570	3434	3729	
	Phosphorus	ppm	ASTM D5185m	1290	1075	1244	
	Zinc	ppm	ASTM D5185m	1640	1284	1638	
	Sulfur	ppm	ASTM D5185m		4387	3648	
	Visc @ 40°C	cSt	ASTM D445		56.6	64.1	







Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0051210

Lab Number : 06216010 Unique Number : 11088874

Diagnosed Test Package : CONST ( Additional Tests: PQ )

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received

**Tested** 

: 20 Jun 2024

: 22 Jun 2024

: 22 Jun 2024 - Wes Davis

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL KendalLeanne@lec1.com

T:

F: (740)373-5570 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)