

NORMAL WEAR NORMAL CONTAMINATION **FLUID CONDITION** NORMAL




Store 9 - Marietta JOHN DEERE 250GLC 1FF250GXENF612031 Swing Drive


JOHN DEERE GL-5 80W90 (2 GAL)

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|-----------------------------------------------------------------|--------------------|------------------|----------------------------|-------------|-------------|----------|----------|
| | Sample Number | 00101 | Client Info | LIIIII/ADII | LEC0050881 | | |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | 18 Jun 2024 | | |
| | Machine Age | hrs | Client Info | | 543 | | |
| | Oil Age | hrs | Client Info | | 543 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | NORMAL | | |
| | DO | | | | 407 | | |
| WEAR | PQ | | ASTM D8184 | 454 | 107 | | |
| Metal levels are typical for a new component breaking in. | Iron | ppm | ASTM D5185m | | 151 | | |
| | Chromium | ppm | ASTM D5185m | | 2 | | |
| | Nickel | ppm | ASTM D5185m ASTM D5185m | >10 | 0 | | |
| | Titanium Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | × 01 | 0 | | |
| | Lead | ppm | ASTM D5185m | | 0 | | |
| | | ppm | ASTM D5185m | | 0 | | |
| | Copper Tin | ppm | ASTM D5185m | | 0 | | |
| | Vanadium | ppm | ASTM D5185m | >10 | 0 | | |
| | White Metal | ppm | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar scalar | *Visual | NONE | NONE | | |
| | | Scala | visuai | | | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >31 | 19 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | >20 | 0 | | |
| There is no indication of any containing to internet of the | Water | | WC Method | >0.1 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.1 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | >51 | 2 | | |
| | Boron | ppm | ASTM D5185m | | 61 | | |
| The condition of the oil is acceptable for the time in service. | Barium | ppm | ASTM D5185m | | 2 | | |
| | Molybdenum | ppm | ASTM D5185m | | 0 | | |
| | Manganese | ppm | ASTM D5185m | | 3 | | |
| | Magnesium | ppm | ASTM D5185m | | 0 | | |
| | Calcium | ppm | ASTM D5185m | | 21 | | |
| | Phosphorus | ppm | ASTM D5185m | | 528 | | |
| | Zinc | ppm | ASTM D5185m | | 8 | | |
| | Sulfur | ppm | ASTM D5185m | | 17686 | | |
| | Visc @ 40°C | cSt | ASTM D445 | | 186 | | |
| | | | | | | | |

Submitted By: JOHN MARTIN







Submitted By: JOHN MARTIN Page 2 of 2

Jun 18/24