



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
AMR-12th Street
 Machine Id
339324 LIEBHERR LH60 1204-86896
 Component
Splitter Box
 Fluid
LIEBHERR GEAR BASIC 90 LS (3 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DJJ0013946	DJJ0017130	DJJ0013872
Sample Date		Client Info		11 Jun 2024	26 Dec 2023	15 Sep 2023
Machine Age	hrs	Client Info		15501	15052	14489
Oil Age	hrs	Client Info		250	250	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	3	11	7
Chromium	ppm	ASTM D5185m	>5	<1	0	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	<1	<1
Lead	ppm	ASTM D5185m	>30	0	0	0
Copper	ppm	ASTM D5185m	>20	<1	2	2
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	<1	6	8
Potassium	ppm	ASTM D5185m	>20	<1	<1	7
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>25	0	1	4
Boron	ppm	ASTM D5185m	0	1	0	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m	0	0	<1	0
Magnesium	ppm	ASTM D5185m	<1	1	0	5
Calcium	ppm	ASTM D5185m	<1	0	0	12
Phosphorus	ppm	ASTM D5185m	2143	2455	2045	2048
Zinc	ppm	ASTM D5185m	<1	0	52	89
Sulfur	ppm	ASTM D5185m	23468	26105	24284	24010
Visc @ 40°C	cSt	ASTM D445	170	195	157	147



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DJJ0013946
Lab Number : 06216156
Unique Number : 11089020
Test Package : MOBCE

Received : 20 Jun 2024
Tested : 24 Jun 2024
Diagnosed : 24 Jun 2024 - Jonathan Hester

ADVANTAGE METALS RECYCLING - 12 STREET
 1153 S. 12TH STREET
 KANSAS CITY, KS
 US 66105
 Contact: JOHN PEEK
 john.peek@advantagerecycling.com
 T: (660)424-9134
 F: (913)621-2766

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)